
Electrostatics —

Part 4-5: Standard test methods for specific applications — Methods for characterizing the electrostatic protection of footwear and flooring in combination with a person

The European Standard EN 61340-4-5:2004 has the status of a British Standard

ICS 17.220.99; 59.080.60

National foreword

This British Standard is the official English language version of EN 61340-4-5:2004. It is identical with IEC 61340-4-5:2004.

The UK participation in its preparation was entrusted to Technical Committee GEL/101, Electrostatics, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible European committee any enquiries on the interpretation, or proposals for change, and keep the UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this committee can be obtained on request to its secretary.

Cross-references

The British Standards which implement international or European publications referred to in this document may be found in the BSI Catalogue under the section entitled "International Standards Correspondence Index", or by using the "Search" facility of the BSI Electronic Catalogue or of British Standards Online.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Summary of pages

This document comprises a front cover, an inside front cover, the EN title page, pages 2 to 16, an inside back cover and a back cover.

The BSI copyright notice displayed in this document indicates when the document was last issued.

Amendments issued since publication

Amd. No.	Date	Comments

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 3 November 2004

© BSI 3 November 2004

ISBN 0 580 44697 2

EUROPEAN STANDARD

EN 61340-4-5

NORME EUROPÉENNE

EUROPÄISCHE NORM

September 2004

ICS 17.220.99 ; 59.080.60

English version

Electrostatics

Part 4-5: Standard test methods for specific applications – Methods for characterizing the electrostatic protection of footwear and flooring in combination with a person (IEC 61340-4-5:2004)

Electrostatique

Partie 4-5: Méthodes d'essai normalisées
pour des applications spécifiques -
Méthodes de caractérisation
de la protection électrostatique
des chaussures et des revêtements de sol
par rapport à une personne
(CEI 61340-4-5:2004)

Elektrostatik

Teil 4-5: Standard-Prüfverfahren für
spezielle Anwendungen –
Verfahren zur Charakterisierung
der elektrostatischen Schutzwirkung
von Schuhwerk und Boden
in Kombination mit einer Person
(IEC 61340-4-5:2004)

This European Standard was approved by CENELEC on 2004-09-01. CENELEC members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CENELEC member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CENELEC member into its own language and notified to the Central Secretariat has the same status as the official versions.

CENELEC members are the national electrotechnical committees of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

CENELEC

European Committee for Electrotechnical Standardization

Comité Européen de Normalisation Electrotechnique
Europäisches Komitee für Elektrotechnische Normung

Central Secretariat: rue de Stassart 35, B - 1050 Brussels

Foreword

The text of document 101/178/FDIS, future edition 1 of IEC 61340-4-5, prepared by IEC TC 101, Electrostatics, was submitted to the IEC-CENELEC parallel vote and was approved by CENELEC as EN 61340-4-5 on 2004-09-01.

The following dates were fixed:

- latest date by which the EN has to be implemented
at national level by publication of an identical
national standard or by endorsement (dop) 2005-06-01
- latest date by which the national standards conflicting
with the EN have to be withdrawn (dow) 2007-09-01

Annex ZA has been added by CENELEC.

Endorsement notice

The text of the International Standard IEC 61340-4-5:2004 was approved by CENELEC as a European Standard without any modification.

CONTENTS

FOER.....	DR OW..	5
1 Scope		4
2 Normative references		4
3 Terms and definitions		4
4 Principle.....		4
5 Atmosphere for conditioning and testing.....		5
6 Test methods for footwear and flooring in combination with a person.....		5
6.1 Floor covering sampling and specimen preparation for laboratory tests.....		5
6.2 Cleaning of footwear for laboratory evaluations and for test on installed floor coverings		6
6.3 Measurement of electrical resistance		6
6.4 Measurement of chargeability		8
7 Test report		9
Annex A (normative) Method of checking calibration of body voltage measuring system		14
Figure 1 – Set-ups for measuring electrical resistance of footwear and flooring in combination with a person.....		11
Figure 2 – Typical body voltage recordings showing points used in calculating mean values		13

ELECTROSTATICS –

Part 4-5: Standard test methods for specific applications – Methods for characterizing the electrostatic protection of footwear and flooring in combination with a person

1 Scope

This part of IEC 61340 specifies test methods for evaluating electrostatic protection provided by a system of footwear and flooring in combination with a person.

The test methods are not intended for individual material or system classification purposes.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60093, Methods of test for volume resistivity and surface resistivity of solid electrical insulating materials

IEC 61340-4-1, Electrostatics – Part 4-1: Standard test methods for specific applications – Electrostatic resistance of floor coverings and installed floors

ISO 1957, Machine-made textile floor coverings – Selection and cutting of specimens for physical tests

3 Terms and definitions

For the purposes of this document, the terms and definitions given in IEC 61340-1-2 apply.

4 Principle

The characterization of a system is achieved by measuring electrical resistance and chargeability of the footwear and flooring in combination with a person. Chargeability is determined using a walking test.

WARNING: Test procedures described in this standard may expose personnel to potentially hazardous electrical conditions. Appropriate electrical hazard reduction practices should be exercised and proper earthing instructions for the equipment used should be followed when performing tests.

5 Atmosphere for conditioning and testing

The following requirements supersede any other specification for the atmosphere for conditioning and testing that may be given in one or more of the documents referred to in this standard.

Unless otherwise agreed, the atmosphere for conditioning and testing for laboratory evaluations shall be (23 ± 2) °C and (12 ± 3) % relative humidity. The conditioning time prior to testing shall be at least 48 h. Textile floor coverings are preferably pre-conditioned for at least 24 h at (20 ± 2) °C and (65 ± 3) % relative humidity prior to conditioning and testing.

During pre-conditioning and conditioning, specimens shall be placed on a rack or other suitable support that allows free circulation of air around them.

Whenever tests are made in uncontrolled conditions, e.g. tests on installed floors, the ambient temperature and relative humidity at the time of measurement shall be recorded.

6 Test methods for footwear and flooring in combination with a person

6.1 Floor covering sampling and specimen preparation for laboratory tests

Sampling and selection of specimens for laboratory tests shall be carried out according to the principles specified in ISO 1957. For the purposes of this standard, the general principles of ISO 1957 apply to all types of floor covering. From each sample select a specimen measuring $(2 \pm 0,1)$ m \times $(1 \pm 0,1)$ m or, in the case of tiles, select sufficient tiles and/or part tiles to make up a single specimen area of $(2 \pm 0,1)$ m \times $(1 \pm 0,1)$ m.

For tests on floor coverings that will be installed with specific earth connections, a groundable point shall be attached to the test specimen in accordance with the manufacturer's instructions, or as otherwise agreed, and in a way that simulates end use earthing methods. For chargeability tests on floor coverings that will be installed without specific earth connections, groundable points shall not be attached to the test specimen.

Sensible electrical resistance measurements cannot be made in the laboratory on floor coverings that will be installed without specific earth connections. Measurement of the electrical resistance of footwear and flooring in combination with a person shall only be made on such floor coverings once installed.

The test specimen shall be mounted or loose-laid on nominal 6,3 mm tempered or standard hardboard, according to the manufacturer's instructions or as otherwise agreed. When mounted or loose-laid on the hardboard there shall be a gap of at least 10 mm between each edge of the specimen and the corresponding edge of the hardboard.

The hardboard shall be clean, smooth and have a point-to-point resistance of greater than 10^{11} Ω when tested under the environmental conditions specified in Clause 5 of this standard and according to the test method specified in IEC 61340-4-1.

Floor finishes shall be tested in conjunction with floor coverings representative of the type for which the finishes are intended. The floor covering shall be prepared and mounted as detailed above. The finish under test shall then be applied to the floor covering in accordance with the manufacturer's instructions or as otherwise agreed. In cases where the manufacturer recommends the use of additional groundable points on the surface of the floor covering, these shall be installed as per the manufacturer's instructions prior to application of the finish, or as otherwise agreed.

NOTE Generally, tests are performed on floor coverings as received, i.e. with finishes and special treatments as appropriate. If the permanency of such finishes and treatments is being investigated, specimens may be submitted to a cleaning process or to practical wear conditions before testing, either for laboratory evaluations or on installed floor coverings.

Test results can be significantly affected by the presence of dirt or other contaminants on the surface of floor coverings. Any cleaning performed on floor coverings shall be carried out as per the manufacturer's instructions prior to conditioning.

6.2 Cleaning of footwear for laboratory evaluations and for test on installed floor coverings

Test results can be significantly affected by the presence of dirt or other contaminants on the soles of footwear. Any cleaning performed on footwear prior to and during testing shall be as follows. If it is required to test footwear "as received" or "as used" then cleaning shall be omitted from the test procedure.

6.2.1 Cleaning materials

6.2.1.1 Sandpaper

P280 grade sandpaper.

6.2.1.2 Scoured cotton cloth

The cloth shall be free from finish and detergent.

6.2.1.3 Ethanol

Concentration ≥ 95 %.

6.2.2 Cleaning procedure

Scrub the sole of each item of footwear using a piece of scoured cotton (6.2.1.2) wetted with ethanol (6.2.1.3) to remove any chemical substance from the surface. When the soles are dry, abrade with a fine sandpaper (6.2.1.1), then remove the dust using a dry piece of scoured cotton. Finally, scrub the sole of each item of footwear again using a fresh piece of scoured cotton wetted with ethanol. This final stage only shall be repeated between each set of measurements. Ensure soles are dry before making measurements.

6.3 Measurement of electrical resistance

6.3.1 Apparatus

6.3.1.1 Resistance measuring apparatus

A self-contained DC resistance meter (ohmmeter) or DC power supply and current meter in the appropriate configuration for resistance measurement, with a ± 10 % accuracy, and fulfilling the following requirements.

NOTE For safety reasons, it should be ensured that the maximum current of the measuring circuit does not exceed 5 mA.

6.3.1.1.1 For laboratory evaluations

The apparatus shall have a circuit voltage while under load of $10\text{ V} \pm 0,5\text{ V}$ for resistance below $1,0\ \Omega \times 10^6\ \Omega$, and $100\text{ V} \pm 5\text{ V}$ for resistance of $1,0\ \Omega \times 10^6\ \Omega$ and above. The measuring range of the apparatus shall be at least one order of magnitude either side of the expected range of resistance being measured. The apparatus shall be used in a manner that ensures unintended earth paths do not influence measurements.

6.3.1.1.2 For acceptance testing

The apparatus shall have an open circuit voltage of $10\text{ V} \pm 0,5\text{ V}$ for resistance below $1,0\ \Omega \times 10^6\ \Omega$, and $100\text{ V} \pm 5\text{ V}$ for resistance of $1,0\ \Omega \times 10^6\ \Omega$ and above. The measuring range of the apparatus shall be at least one order of magnitude either side of the expected range of resistance being measured. The apparatus shall be used in a manner that ensures unintended earth paths do not influence measurements.

Laboratory evaluation equipment as specified in 6.3.1.1.1 may also be used for acceptance testing. In case of dispute, only a laboratory evaluation apparatus shall be used.

6.3.1.2 Hand-held electrode

A stainless steel round stock or tube, approximately 25 mm diameter and 75 mm in length with a banana plug receptacle or screw connector attached to one end of the cylinder.

6.3.2 Test procedure

Wear the test footwear on both feet for at least 10 min prior to the commencement of testing.

Connect the negative lead of the resistance measuring apparatus (6.3.1.1) to the groundable point of the test floor covering (laboratory tests) or to earth (tests on installed floor coverings). Connect the other lead to the hand-held electrode (6.3.1.2). Stand with both feet on the test floor covering and firmly grasp the hand-held electrode (see Figure 1).

Starting with the voltage set to 10 V, take a reading of the resistance $15\text{ s} \pm 2\text{ s}$ after applying the test voltage. If the value exceeds $10^6\ \Omega$, select 100 V and repeat the measurement. Record the reading which matches the voltage and resistance range specified in 6.3.1.1. If the resistance falls below $10^6\ \Omega$ when making a measurement using 100 V, this reading shall be the one recorded.

Repeat the measuring procedure with only the left foot in contact with the test floor covering and with the right foot held in the air about 150 mm above the floor covering.

Repeat the measuring procedure with only the right foot in contact with the test floor covering and with the left foot held in the air about 150 mm above the floor covering.

For laboratory tests, measurements shall be made at five different locations distributed evenly over the area of the test specimen.

For tests on installed floor coverings, at least five measurements shall be made for each floor covering material. For large floor areas at least five measurements per 500 m² of each floor covering material shall be made. Where there is evidence of wear, chemical or water spillage or visible dirt, then at least three measurements shall be made on such affected areas.

6.4 Measurement of chargeability

6.4.1 Apparatus

6.4.1.1 Body voltage measuring system

An electrostatic voltmeter, a hand-held electrode (6.3.1.2) and an autographic recorder meeting the following requirements:

- a) input resistance of electrostatic voltmeter $\geq 10^{14} \Omega$;
- b) input capacitance of electrostatic voltmeter, hand-held electrode and connecting leads $\leq 30 \text{ pF}$;
- c) system response time shall be such that full-scale deflection on the recorder is reached within 0,25 s;
- d) system resolution shall be at least one-tenth of the voltage level concerned; for example, for the comfort of personnel, body voltages of several kilovolts are considered, in which case the resolution of the measuring system shall be 0,1 kV; in the electronics industry body voltages of 100 V are considered, in which case the resolution of the measuring system shall be 10 V;
- e) system accuracy of $\pm 10 \%$.

6.4.1.2 Ionizing source

Capable of eliminating electrostatic charge from the surface of footwear and floor covering specimens.

NOTE All relevant safety precautions and regulations should be observed.

6.4.2 Test procedure

For laboratory evaluations on floor coverings that will be installed with specific earth connections, measurements shall be made on specimens fitted with suitable groundable points (see 6.1) and connected to earth. When carrying out laboratory evaluations on floor coverings that will be installed without specific earth connections, groundable points shall not be attached to test specimens, which shall remain isolated from earth whilst measurements are made.

For laboratory evaluations, the procedures described in 6.4.2.1 to 6.4.2.4 inclusive shall be carried out three times for each combination of footwear and floor covering to be tested.

For tests on installed floor coverings, the procedures described in 6.4.2.1 to 6.4.2.4 inclusive shall be carried out at least five times for each combination of footwear and floor covering to be tested. For large floor areas, procedures 6.4.2.1 to 6.4.2.4 inclusive shall be carried out at least five times per 500 m² of each floor covering material. Where there is evidence of wear, chemical or water spillage or visible dirt, then at least three of these measurements shall be made on such affected areas.

6.4.2.1 Discharging test items

Eliminate any residual electrostatic charge on the footwear and floor covering using the ionizing source (6.4.1.2). Loose-laid specimens for laboratory evaluations shall be discharged on both sides before re-positioning them carefully without sliding on the support material (6.1).

6.4.2.2 Donning footwear

The operative shall don the footwear whilst sitting on a nearby seat. The operative shall be earthed and the soles of the footwear discharged using the ionizing source (6.4.1.2). The operative then stands on the floor covering without sliding.

Footwear shall be fastened securely as in normal use.

6.4.2.3 Zeroing the system

The operative shall take hold of the hand-held electrode connected to the body voltage measuring system (6.4.1.1) and shall momentarily touch an earth bonding point to zero the system.

6.4.2.4 Walking

The operative shall walk on the floor covering at a rate of two steps per second whilst maintaining the body facing in the same direction throughout the test. The operative shall cover as much of the test area as possible by walking forwards and backwards, but avoiding scuffing or pivoting. The test area is the whole area of the floor covering specimen for laboratory evaluations, or an equivalent size area of installed flooring. The stepping action shall maintain the sole of the footwear parallel to the floor covering specimen at all times while lifting the footwear between 50 mm and 80 mm. For laboratory evaluations, the operative shall not come closer than 0,5 m to the wall, or any object in the room, and shall continue walking until the peak voltage ceases to rise, or for 60 s, whichever occurs first.

After walking, the operative shall remove the footwear and, if required, clean the soles (6.2).

6.4.3 Calculation and expression of results

For each walking measurement, the arithmetic mean of the five highest valleys and the arithmetic mean of the five highest peaks shall be calculated (see Figure 2). The results shall be expressed in relation to the voltage of concern and the resolution of the measuring system. For example, for personnel comfort, the results may be expressed in kilovolts to the nearest 0,1 kV, or for the electronics industry, the results may be expressed in volts to the nearest 10 V.

7 Test report

The test report shall include at least the following information:

- a) reference to this standard;
- b) all the information necessary for complete identification of test samples;
- c) identification of instrumentation used;
- d) date of testing;

- e) atmosphere for pre-conditioning, conditioning and testing as follows:
 - for laboratory evaluations: temperature and relative humidity during pre-conditioning (if used), conditioning and testing, and the duration of any pre-conditioning and conditioning;
 - for tests on installed floors: temperature and relative humidity during testing;
- f) details of any cleaning or finishing procedures for both footwear and floor covering materials;
- g) details of procedures and materials used to fix specimens to hardboard;
- h) details of procedures and materials used to fix groundable points to specimens;
- i) type of measurement: electrical resistance or chargeability;
- j) all individual results for each type of measurement on each specimen;
- k) average of all results for each type of measurement on each sample;
- l) any operations not specified in this part of IEC 61340, or in any standard to which normative reference is made, or regarded as optional, which might have affected the results.





Figure 1a – Laboratory set-up

IEC 919/04




IEC 920/04

Figure 1b – Test set-up for installed flooring

Key


- 1 hand-held electrode (6.3.1.2)
- 2 resistance measuring apparatus (6.3.1.1)
- 3 groundable point (6.1)
- 4 floor covering under test
- 5 support material (6.1)
- 6 installed flooring
- 7 building earth

Figure 1 – Set-ups for measuring electrical resistance of footwear and flooring in combination with a person



IEC 921/04

Figure 2a – Positive polarity body voltage recording



IEC 922/04

Figure 2b – Negative polarity body voltage recording

Key

P1 to P5: five highest peaks

T1 to T5: five highest valleys

Figure 2 – Typical body voltage recordings showing points used in calculating mean values

Annex A (normative)

Method of checking calibration of body voltage measuring system

A.1 Static calibration

The body voltage measuring system zero voltage point is checked by connecting the hand-held electrode to an earth bonding point. After being disconnected from the earth bonding point, the system is then checked by connecting the hand-held electrode to an output terminal of a stable d.c. voltage supply. At least three voltage levels of both positive and negative polarity shall be confirmed, for example 1 kV, 2 kV and 5 kV; or 100 V, 200 V and 500 V.

A.2 Dynamic calibration

The body voltage measuring system is calibrated by a dynamic method using either a signal generator or a manual switching procedure.

A.2.1 Signal generator method

The hand-held electrode is connected to the output terminal of a signal generator with an output amplitude appropriate to the body voltages to be measured, for example $1 \text{ kV} \pm 0,1 \text{ kV}$ or $100 \text{ V} \pm 10 \text{ V}$. The output frequency shall be 2 Hz with a rise/fall time of not greater than 2 ms. The procedure is carried out with both positive and negative polarity. Any overshoot or undershoot in the autographic recording of the voltage shall not exceed 10 % of the applied voltage amplitude.

A.2.2 Manual switching method

The voltage supply for this procedure shall have a suitable over-current protection circuit. Additional protection for the operative may be obtained by placing a high voltage tolerant resistor of $1 \text{ M}\Omega$ to $10 \text{ M}\Omega$ in series with the output of the voltage supply.

An operative gripping the hand-held electrode in one hand stands on an insulating platform of volume resistivity $\geq 10^{14} \text{ }\Omega\text{m}$, measured according to IEC 60093. With the other hand, the operative alternately touches an output terminal from a stable DC voltage supply and then an earth bonding point. The output from the voltage supply is set as appropriate to the body voltages to be measured, for example $1 \text{ kV} \pm 0,1 \text{ kV}$ or $100 \text{ V} \pm 10 \text{ V}$. The operative charges and discharges at a rate of two cycles per second. A metronome is used to provide the cycle for switching. The procedure is carried out with both positive and negative polarity. Any overshoot or undershoot in the autographic recording of the voltage shall not exceed 10 % of the applied voltage amplitude.

Bibliography

IEC 61340-1-2, Electrostatics – Part 1-2: Definitions of all parts of the IEC 61340 series ¹

¹ Under consideration.

Annex ZA (normative)

Normative references to international publications with their corresponding European publications

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

NOTE Where an international publication has been modified by common modifications, indicated by (mod), the relevant EN/HD applies.

Publication	Year	Title	EN/HD	Year
IEC 60093	- 1)	Methods of test for volume resistivity and surface resistivity of solid electrical insulating materials	HD 429 S1	1983 2)
IEC 61340-4-1	- 1)	Electrostatics Part 4-1: Standard test methods for specific applications - Electrical resistance of floor coverings and installed floors	EN 61340-4-1	2004 2)
ISO 1957	- 1)	Machine-made textile floor coverings - Selection and cutting of specimens for physical tests	-	-

1) Undated reference.

2) Valid edition at date of issue.

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001.

Fax: +44 (0)20 8996 7001. Email: orders@bsi-global.com. Standards are also available from the BSI website at <http://www.bsi-global.com>.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre. Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: info@bsi-global.com.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001.

Email: membership@bsi-global.com.

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsi-global.com/bsonline>.

Further information about BSI is available on the BSI website at <http://www.bsi-global.com>.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager. Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553. Email: copyright@bsi-global.com.