
Specification and qualification of welding procedures for metallic materials — Welding procedure test —

Part 11: Electron and laser beam
welding

The European Standard EN ISO 15614-11:2002 has the status of a
British Standard

ICS 25.160.10

National foreword

This British Standard is the official English language version of EN ISO 15614-11:2002. It is identical with ISO 15614-11:2001.

The UK participation in its preparation was entrusted to Technical Committee WEE/36, Approval testing of welding procedures and welders, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible European committee any enquiries on the interpretation, or proposals for change, and keep the UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this committee can be obtained on request to its secretary.

Cross-references

The British Standards which implement international or European publications referred to in this document may be found in the BSI Standards Catalogue under the section entitled "International Standards Correspondence Index", or by using the "Find" facility of the BSI Standards Electronic Catalogue.

A British Standard does not purport to include all the necessary provisions of a contract. Users of British Standards are responsible for their correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Summary of pages

This document comprises a front cover, an inside front cover, the EN ISO title page, pages 2 to 28, an inside back cover and a back cover.

The BSI copyright date displayed in this document indicates when the document was last issued.

This British Standard, having been prepared under the direction of the Engineering Sector Policy and Strategy Committee, was published under the authority of the Standards Policy and Strategy Committee on 28 March 2002

Amendments issued since publication

Amd. No.	Date	Comments

ICS 25.160.10

English version

Specification and qualification of welding procedures for metallic materials - Welding procedure test - Part 11: Electron and laser beam welding (ISO 15614-11:2002)

Descriptif et qualification d'un mode opératoire de soudage pour les matériaux métalliques - Epreuve de qualification d'un mode opératoire - Partie 11: Soudage par faisceau d'électrons et par faisceau laser (ISO 15614-11:2002)

Anforderung und Qualifizierung von Schweißverfahren für metallische Werkstoffe - Schweißverfahrensprüfung - Teil 11: Elektronen- und Laserstrahlschweißen (ISO 15614-11:2002)

This European Standard was approved by CEN on 2 May 2001.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

	page
Foreword.....	3
Introduction	4
1 Scope	5
2 Normative references	5
3 Terms and definitions.....	6
4 Welding procedure specification (WPS).....	6
5 Welding procedure test.....	6
6 Test piece.....	6
6.1 General.....	6
6.2 Shape and dimensions of test pieces.....	6
6.3 Welding of test pieces.....	11
7 Examination and testing	11
7.1 Extent of examination and testing	11
7.2 Location and cutting of test specimens.....	14
7.3 Non-destructive examination.....	18
7.4 Destructive tests.....	18
7.5 Re-testing.....	20
8 Range of qualification	20
8.1 General.....	20
8.2 Related to the manufacturer	20
8.3 Related to the equipment.....	20
8.4 Related to the jigs, fixtures and tooling	20
8.5 Related to the parent material	20
8.6 Related to the filler materials.....	21
8.7 Related to the joint geometry	21
8.8 Related to the presence of a weld backing	21
8.9 Related to the weld type.....	21
8.10 Related to the welding position.....	22
8.11 Related to the welding parameters	22
8.12 Related to preheating	22
8.13 Related to post weld heat treatment.....	22
8.14 Related to the number of passes	22
8.15 Duration of validity	22
9 Welding Procedure Qualification Record (WPQR)	22
Annex A (informative) Welding Procedure Qualification Record form (WPQR)	23
Annex ZA (normative) List of ISO corresponding standards to European Standards given in clause 2	27
Annex ZB (informative) Clauses of this European Standard addressing essential requirements or other provisions of EU directives.....	28

Foreword

The text of EN ISO 15611:2002 has been prepared by Technical Committee CEN/TC 121 "Welding", the secretariat of which is held by DS, in collaboration with Technical Committee ISO/TC 44 "Welding and allied processes".

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2002, and conflicting national standards shall be withdrawn at the latest by September 2002.

This European Standard has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EU Directive(s).

For relationship with EU Directive(s), see informative annex ZB, which is an integral part of this standard.

Annexes A and ZB are informative.

The annex ZA is normative.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

Introduction

Qualification of welding procedures serves to demonstrate that production operations fully comply with the agreed welding procedure including preliminary and subsequent treatment.

Before a particular welding procedure is used in a production operation, the manufacturer should determine and document the suitability of the Welding Procedure Specification (WPS) to produce a weld of the required quality.

To date the suitability of welding procedures has been established for weldments as part of the quality assurance activity. Until now, establishing the suitability of welding procedures by weld procedure testing was carried out and documented only for weldments involving safety and the public interest. The European harmonisation of the provision for welding procedure tests is currently being sought by means of European Standards. In this way greater confidence will be generated for the customer by the manufacturer.

The proofs also serve as the basis for the mutual recognition of performance reached by the relevant authorities. In this standard, the term "welding procedure" comprises all the activities which influence the welding result, such as preparation, welding parameters, post treatment and reworking.

1 Scope

This European Standard specifies how a welding procedure specification for electron or laser beam welding is qualified by a welding procedure test.

This standard is a part of a series of standards, details of this series are given in prEN ISO 15607, annex A.

It defines the conditions for the execution of welding procedure qualification tests and the limits of validity of a qualified welding procedure for all practical welding operations within the range of variables listed in clause 8.

Tests shall be carried out in accordance with this standard together with additional tests when specified.

This standard applies to metallic materials, irrespective of the shape of the parts, their thicknesses, manufacturing method (rolling, forging, casting, sintering, etc.) and their heat treatment. It covers unlimitedly the production of new parts and repair work.

2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

EN 571-1, Non destructive testing — Penetrant testing — Part 1 : General principles.

EN 895, Destructive tests on welds in metallic materials — Transverse tensile test.

EN 910, Destructive tests on welds in metallic materials — Bend tests.

EN 970, Non-destructive examination of fusion welds — Visual examination.

EN 1043-2, Destructive test on welds in metallic materials — Hardness test — Part 2: Micro hardness testing on welded joints.

EN 1290, Non-destructive examination of welds — Magnetic particle examination of welds.

EN 1321, Destructive tests on welds in metallic materials — Macroscopic and microscopic examination of welds.

EN 1435, Non-destructive examination of welds — Radiographic examination of welded joints.

EN 1714, Non destructive examination of welds — Ultrasonic examination of welded joints.

EN ISO 6947, Welds — Working positions — Definitions of angles of slope and rotation (ISO 6947:1993).

prEN ISO 15607, Specification and approval of welding procedures for metallic materials – General rules (ISO/DIS 15607:2000).

prEN ISO 15609-3:2000, Specification and approval of welding procedures for metallic materials - Welding procedure specification — Part 3: Electron beam welding (ISO/DIS 15609-3:2000).

prEN ISO 15609-4:2000, Specification and approval of welding procedures for metallic materials - Welding procedure specification — Part 4: Laser beam welding (ISO/DIS 15609-4:2000).

EN ISO 13919-1, Welding — Electrons and laser beam welded joints — Guidance on quality levels for imperfections — Part 1: Steel (ISO 13919-1:1996).

prEN ISO 13919-2, Welding — Electron and laser beam welded joints — Guidance on quality levels for imperfections — Part 2: Aluminium and its weldable alloys (ISO/FDIS 13919-2:1999).

3 Terms and definitions

For the purposes of this European Standard, the terms and definitions given in prEN ISO 15607, prEN ISO 15609-3 and prEN ISO 15609-4 apply.

4 Welding procedure specification (WPS)

A pWPS (preliminary welding procedure specification) shall be prepared in accordance with prEN ISO 15609-3 for electron beam welding and prEN ISO 15609-4 for laser beam welding. It shall specify the tolerances for all the relevant parameters.

A WPS shall be classified as pWPS until it is qualified in accordance with this standard.

The welding procedure specification (WPS) shall give details on how a welding operation is to be performed, including tacking and fixturing.

5 Welding procedure test

The manufacture and testing of test pieces shall be in accordance with clauses 6 and 7 of this standard.

In order to take into account the service performance needs of the products, the qualification may be made according to any of the acceptance levels B, C or D as defined in EN ISO 13919-1 for steels or in prEN ISO 13919-2 for aluminium and its alloys.

The quality level necessary in each case should be specified by the application standard or the responsible designer.

6 Test piece

6.1 General

The assembly to which the electron or laser beam welding procedure applies in production may be represented by one or more standardized test pieces as defined in 6.2.

6.2 Shape and dimensions of test pieces

The test pieces shall be of sufficient size to ensure an adequate heat distribution and for the application of non-destructive and/or destructive tests.

The test piece shall be designed to represent, as far as possible, the component and joint geometry and shall be specified.

One or more additional test pieces or a longer test piece than the minimum size, may be used in order to allow for extra and/or for re-testing specimens, according to 7.5.


For plate material, the principal direction of rolling shall be marked on the test piece, if requested by the application standard or the specification.

The thickness and/or pipe outside diameter of the test pieces shall be selected in accordance with 8.5.2.1 to 8.5.2.2.

Unless otherwise specified, the shape and minimum dimensions of the test piece shall be as defined hereafter. Nonetheless, the length of the test piece shall be such as to permit the appropriate number of test specimens (as given in Tables 1 to Table 3) to be prepared.

6.2.1 Linear butt weld

The test piece shall be in accordance with Figure 1.



Key

1 Edge preparation and fit-up as detailed in the preliminary Welding Procedure Specification (pWPS)

$a = 3 \times t$; minimum value 150 mm $b = 6 \times t$; minimum value 300 mm

t = thickness of the thinner material in a dissimilar thickness joint

Figure 1 — Test piece for a linear butt weld

6.2.2 Circular butt weld


The test piece shall be in accordance with Figures 2 a) or 2 b). When small pipe diameters are used, several test pieces may be necessary.

In cases where the diameter, D , of the part is greater than 150 mm and $D > 20 t$, the qualification of the procedure may be achieved by welding a linear test piece. The test shall be designed to incorporate the weld overlap and slope down areas.

NOTE The word pipe is used to mean "pipe", "tube" or "hollow section".

6.2.2.1 Radial butt weld in pipe (in accordance with Figure 2 a)

6.2.2.2 Axial weld in pipe to pipe or pipe to plate (in accordance with Figure 2 b)




Key

1 Edge preparation and fit-up as detailed in the preliminary Welding Procedure Specification (pWPS)

$a = 3 \times t$; minimum value 150 mm $D =$ outside dimension of the pipe

$t =$ wall thickness of the thinner pipe in a dissimilar thickness joint

a) Test piece for a radial butt weld in pipe

**Key**

1 Edge preparation and fit-up as detailed in the preliminary Welding Procedure Specification (pWPS)

a = minimum plate dimension or component diameter

D = outside dimension of the pipe

a $D + 6 t$; minimum value $D + 150 \text{ mm}$

t = plate thickness

b) Test piece for an axial weld in pipe to pipe or pipe to plate

Figure 2 — Test pieces for circular butt welds


6.2.3 Other types

6.2.3.1 T-joint

The test piece shall be in accordance with Figure 3.

T-joint of the following types can be made :

- a) T-butt from one side ;
- b) T-butt from two sides ;
- c) fillet weld (partial penetration) from one or two side(s) ;
- d) a stake weld(s).



Key

1 Edge preparation and fit-up as detailed in the preliminary Welding Procedure Specification (pWPS)

For a), b) and c) configurations :

a_1 $6 \times t_1$; minimum value 50 mm

a_2 $6 \times t_1$; minimum value 100 mm

b 300 mm

t_1 and t_2

t_1 and t_2 = plate thicknesses

For d) configuration :

a_1 $6 \times t_2$; minimum value 50 mm

a_2 $6 \times t_2$; minimum value 100 mm


b 300 mm

Figure 3 — Test piece for a T-joint

6.2.3.2 Lap weld

The test piece for a two layer lap weld shall be in accordance with the assembly shown in Figure 4.

The weld may be either partial or full penetration through all sheets or plates.



Key

- 1 Edge preparation and fit-up as detailed in the preliminary Welding procedure specification (pWPS)
- a $4 \times (t_1 + t_2)$; minimum value 100 mm
- b 300 mm
- t_1 and t_2 = plate thicknesses

NOTE The joint may also consist of three or more overlapping sheets.

Figure 4 — Test piece for a lap weld

6.3 Welding of test pieces

Preparation and welding of test pieces representative of the application shall be carried out in accordance with the pWPS and under the same conditions as those used for welding production.

If tack welds are to be fused into the final joint, they shall be included in the test piece.

Welding and testing of the test pieces shall be witnessed by an examiner or an examining body.

7 Examination and testing

7.1 Extent of examination and testing

Examination and testing include the non-destructive examination (NDE) and destructive testing which shall be in accordance with the requirements of Tables 1, 2 or 3, as appropriate.

Table 1 — Examination and tests for welds in accordance with acceptance level B

Test piece	Type of examination and test	Extent of examination and test	See table footnote
Butt weld Figures 1, 2 a) and 2 b)	- Visual examination	100 %	-
	- Radiographic examination	100 %	a
	- Ultrasonic examination	100 %	a
	- Surface crack detection	100 %	b
	- Metallographic examination	1 section minimum	c
	- Hardness test	if required	d
	- Transverse bend test	if required : 2 root bend specimens and 2 face bend specimens	e
	- Longitudinal bend test	if required : 1 root bend specimen and 1 face bend specimen	f
	- Transverse tensile test	2 specimens	g
- Toughness test	1 set of specimens	h	
T-joint Figure 3 i	- Visual examination	100 %	-
	- Surface crack detection	100 %	b
	- Ultrasonic examination	100 %	j
	- Hardness test	if required	-
	- Metallographic examination	2 sections	c
	- Other tests	if required	
Lap weld Figure 4	- Visual examination	100 %	-
	- Metallographic examination	2 sections	c
	- other tests (e.g. hardness, leak test, peel test, ...)	if required	-

a Radiographic and/or ultrasonic examination.

b Penetrant testing or magnetic particle examination. For non-magnetic materials, penetrant testing.

c One section required for a butt weld in plate ; three sections required for a butt weld in pipe (see Figure 6) ; for each standard welding position in accordance with EN ISO 6947. These sections shall be subjected to macroscopic and microscopic examinations.

d Hardness tests are required depending on base and filler material.

e The two root and two face bend test specimens should be preferably replaced by four side bend test specimens when $t \geq 20$ mm.

f Longitudinal bend tests may be used in the case of flat heterogeneous assemblies and replace transverse bend tests.

g For butt welds according to Figure 2 b) transverse tensile tests are not appropriate.

h Depending on the material and the thicknesses and except for butt weld according to Figure 2 b) one or more sets can be taken from the weld metal and from the HAZ. These tests are relevant when the parent metal has a specified toughness or when prescribed by the application standard. If no testing temperature is specified, the test shall be carried out at room temperature. See also 7.4.3. In case of use of any kind of filler material, additional toughness test specimens shall be taken from the top and the root area.

i When the WPS has not been qualified by other means, additional tests permitting the verification of the mechanical properties of the assembly shall be considered.

j Unless ultrasonic beam attenuation or material thickness causes ultrasonic examination to be impracticable.

Table 2 — Examination and tests for welds in accordance with acceptance level C

Test piece	Type of examination and test	Extent of examination and test	See table footnote
Butt weld Figures 1, 2 a) and 2 b)	- Visual examination - Radiographic examination - Ultrasonic examination - Surface crack detection - Metallographic examination - Hardness test - Transverse bend test - Longitudinal bend test - Transverse tensile test	100 % 100 % 100 % 100 % 1 section minimum if required if required : 2 root bend specimens and 2 face bend specimens if required : 1 root bend specimen and 1 face bend specimen 2 specimens	- a a b b - e f g
T-joint Figure 3 ^h	- Visual examination - Surface crack detection - Ultrasonic examination - Hardness test - Metallographic examination - Other tests	100 % 100 % 100 % if required 1 section minimum if required	- b i - c -
Lap weld Figure 4	- Visual examination - Metallographic examination - other tests (e.g. hardness, leak test, peel test, ...)	100 % 1 section minimum if required	- c -
a	Radiographic and/or ultrasonic examination.		
b	Penetrant testing or magnetic particle examination. For non-magnetic materials, penetrant testing.		
c	One section required for a butt weld in plate ; three sections required for a butt weld in pipe (see Figure 6) ; for each standard welding position in accordance with EN ISO 6947. These sections shall be subjected to macroscopic examination only.		
d	Hardness tests are required depending on base and filler material.		
e	The two root and two face bend test specimens should be preferably replaced by four side bend test specimens when $t \geq 20$ mm.		
f	Longitudinal bend tests may be used in the case of flat heterogeneous assemblies and replace transverse bend tests.		
g	For butt welds according to Figure 2 b) transverse tensile tests are not appropriate.		
h	When the WPS has not been qualified by other means, additional tests permitting the verification of the mechanical properties of the assembly shall be considered.		
i	Unless ultrasonic beam attenuation or material thickness causes ultrasonic examination to be impracticable.		

Table 3 — Examination and tests for welds in accordance with acceptance level D

Test piece	Type of examination and test	Extent of examination and test	See table footnote
Butt weld Figures 1, 2 a) and 2 b)	- Visual examination - Radiographic examination - Ultrasonic examination - Surface crack detection - Metallographic examination	100 % if required if required if required 1 section minimum	- - - - a
T-joint Figure 3	- Visual examination - Surface crack detection - Ultrasonic examination - Metallographic examination	100 % if required if required 1 section minimum	- - - a
Lap weld Figure 4	- Visual examination - Metallographic examination	100 % 1 section minimum	- a
^a One section required for a butt weld in plate ; three sections required for a butt weld in pipe (see Figure 6) ; for each standard welding position in accordance with EN ISO 6947. These sections shall be subjected to macroscopic examination only.			

7.2 Location and cutting of test specimens

The location of test specimens shall be in accordance with Figures 5 to 8.

In the case of the overlap area (slope up and slope down) two metallographic test specimens shall be taken from the following positions :


one in the overlap ;

one in the slope down area.

If it is not possible to take these two specimens because the extension of the overlap before start of slope down is too small, only one specimen shall be taken in the slope down area.

Other test specimens may be taken from this area if required in the specification.


Test specimens shall be taken after non-destructive examination (NDE) has shown satisfactory results. It is permitted to take test specimens from locations avoiding areas showing acceptable imperfections as defined below in 7.3.2.



Key

- 1 Area 1 for 1 tensile specimen ; 1 root and 1 face bend specimen or 2 side bend specimens.
- 2 Area 2 for impact and additional test specimens if required.
- 3 Area 3 for 1 tensile specimen ; 1 root and 1 face bend specimen or 2 side bend specimens.
- 4 Area 4 for 1 metallographic specimen/hardness (if required) .
- 5 Discard : if $t \leq 25$ mm : discard 25 mm, if $t > 25$ mm : discard 50 mm minimum
- 6 Welding direction

Figure 5 — Location of test specimens for a linear butt weld




Key

- 1 Area 1^a for 1 tensile specimen ; 1 root and 1 face bend specimen or 2 side bend specimens.
- 2 Area 2^a for impact and additional test specimens if required.
- 3 Area 3^a for 1 tensile specimen ; 1 root and 1 face bend specimen or 2 side bend specimens.
- 4 Area 4^a for 1 metallographic specimen/hardness (if required).
- 5 Area 5 for 1 metallographic specimen.
- 6 Area 6 for 1 metallographic specimen.
- R Location of beginning of overlap.
- E Location of beginning of slope down.
- F Location of end of slope down.


^a Areas 1, 2, 3 and 4 shall be located outside the RE and EF zones and additionally metallographic examination for each standard welding position (for orbital welding only).

Figure 6 — Location of test specimens for a butt weld in pipe

**Key**

- 1 Discard : if (t_1 or t_2) > 25 mm : discard 50 mm minimum
 25 mm : discard 25 mm ; if (t_1 or t_2) > 25 mm : discard 50 mm minimum
- 2 Metallographic/Hardness test specimens (if required)
- 3 Other tests (if required)
- 4 Welding direction


a) in a T-butt from one or two sides or a fillet weld (partial penetration) from one or two sides

**Key**

- 1 Discard : if (t_1 or t_2) > 25 mm : discard 50 mm minimum
 25 mm : discard 25 mm ; if (t_1 or t_2) > 25 mm : discard 50 mm minimum
- 2 Metallographic/Hardness test specimens (if required)
- 3 Other tests (if required)
- 4 Welding direction

b) in a stake weld(s)

Figure 7 — Location of test specimens in a T-joint



Key

- 1 Discard : if $(t_1 + t_2) > 25 \text{ mm}$: discard 50 mm minimum
 if $(t_1 + t_2) \leq 25 \text{ mm}$: discard 25 mm ; if $(t_1 + t_2) > 25 \text{ mm}$: discard 50 mm minimum
- 2 Metallographic /Hardness test specimens (if required)
- 3 Other tests (if required)
- 4 Welding direction

Figure 8 — Location of test specimens in a lap weld

7.3 Non-destructive examination

7.3.1 Method

After any required post-weld heat treatment and prior to the cutting of test specimens, all test pieces shall be subjected to visual surface examination and non-destructive examination in accordance with the Tables of 7.1.

Depending upon joint geometry and material, non-destructive examination shall be carried out according to EN 970 (visual examination), EN 1435 (radiographic examination), EN 1714 (ultrasonic examination), EN 571-1 (penetrant testing), magnetic particle examination (EN 1290).

7.3.2 Acceptance level

A welding procedure is qualified if any imperfections detected in the test piece are within the specified limits given in the following standards, at the agreed acceptance level :

EN ISO 13919-1, without the restrictive limitation of thickness, for steels ;

prEN ISO 13919-2, for aluminium and its alloys.

7.4 Destructive tests

7.4.1 Transverse tensile testing

7.4.1.1 Method

Transverse tensile testing shall be performed at room temperature or other agreed test temperature. Test specimens and testing for transverse tensile testing for butt joints shall be in accordance with EN 895.

For pipes $> 50 \text{ mm}$ outside diameter, the excess weld metal shall be removed on both faces to give the test specimen a thickness equal to the wall thickness of the pipe.

For pipes $\leq 50 \text{ mm}$ outside diameter, and when full section small diameter pipes are used, the excess weld metal may be left undressed on the inside surface of the pipe.

7.4.1.2 Acceptance level

For welds in acceptance level B or C, the tensile strength of the specimen shall not be lower than the minimum value specified for the application and included in the pWPS.

7.4.2 Bend testing

7.4.2.1 Method

Test specimens and test method for bend testing for butt joints shall be in accordance with EN 910.

For dissimilar metal joints or heterogeneous butt joints in plates, one root and one face longitudinal bend test specimens may be used instead of the transverse bend test specimens.

The former diameter and the method of testing shall be specified in the pWPS.

The test specimens should be bent through 180° unless the strength and/or ductility of the parent metal or weld metal impose other limitations.

7.4.2.2 Acceptance level

During testing, unless otherwise specified, the test specimens shall not reveal any imperfection of a length > 3 mm in any direction. Imperfections not initiated by a weld defect, appearing at the corners of a test specimen during testing, shall be ignored in the evaluation.

7.4.3 Toughness testing

Due to difficulties in carrying out valid toughness tests in narrow electron beam and laser welds the test to be used and the acceptance level shall be defined in the specification.

7.4.4 Hardness testing

7.4.4.1 Method

The Vickers micro hardness testing shall be carried out in accordance with EN 1043-2.

7.4.4.2 Acceptance level

The indentation load and the value of hardness measured shall conform with the requirements laid down at the design stage for the part being fabricated and with the provisions of the application standard.

7.4.5 Metallographic examination

7.4.5.1 Method

Macroscopic examination shall be carried out in accordance with EN 1321 using either naked eyes or a magnification at up to x 50 as appropriate.

Macro examination shall include part of the unaffected parent metal. Microscopic examination shall be carried out in accordance with EN 1321.

For welds of acceptance level B the examinations shall include macroscopic and microscopic examinations. They shall be accompanied with supporting photographs.

For welds of acceptance level C and D, the examinations shall be macroscopic only and shall be accompanied with supporting photographs for class C and may be accompanied with supporting photographs for class D.

7.4.5.2 Acceptance level

The acceptance levels shall be as defined in the specification and as suggested in EN ISO 13919-1 for steels, prEN ISO 13919-2 for aluminium and its alloys.

7.5 Re-testing

If the test piece fails to comply with any of the requirements for visual examination or other non-destructive examinations specified in 7.3.2, one further test piece shall be welded and subjected to the same examination.

If this additional test piece does not comply with the relevant requirements, the pWPS shall be regarded as not capable of complying with the requirements of this standard without modification.

If any test specimen fails to comply with the relevant requirements of 7.4 due only to an overlooked imperfection, one further test specimen shall be obtained for each one that failed. The test specimen can be taken from the same test piece if there is sufficient material available, or from a new test piece subjected to the same testing conditions.

If the additional test specimen does not comply with the relevant requirements, the pWPS shall be regarded as not capable of complying with the requirements of this standard without modification.

8 Range of qualification

8.1 General

All the conditions of validity stated below shall be met independently of each other.

Changes outside of the ranges specified shall require a new welding procedure test.

8.2 Related to the manufacturer

A qualification of a WPS obtained by a manufacturer is valid only for welding in workshops under the same technical and quality control of that manufacturer.

8.3 Related to the equipment

A qualification of a WPS is valid only for the electron gun and laser system type used, according to 4.11 of prEN ISO 15609-3:2000, WPS for electron beam welding, and of prEN ISO 15609-4, WPS for laser beam welding.

This qualification can be extended to similar equipment from the same manufacturer using selected tests defined in the specification.

8.4 Related to the jigs, fixtures and tooling

A qualified WPS is valid only for jigs, fixtures or tooling specified in the WPS

8.5 Related to the parent material

8.5.1 Grades

A qualified WPS is valid only for the grade of parent material (or grades, in the case of heterogeneous assemblies) of the test piece.

The qualification could be extended to equivalent grades defined in the specification.

8.5.2 Geometry of the assembly

8.5.2.1 Thickness

t : thickness of the test piece ;

s : depth of penetration ;

s may be greater than t (presence of an external backing) or smaller (presence of a backing weld or sealing weld).

A procedure test carried out on a thickness "t" for a depth of penetration "s" shall qualify the thicknesses for the range of qualification given in Table 4.

Table 4 — Range of qualification for thickness

Dimensions in millimetres

Depth of penetration	Acceptance level B	Acceptance level C	Acceptance level D
s < 5	t 20 %	t 25 %	t 30 %
5 ≤ s ≤ 25	t 15 %	t 20 %	t 25 %
s > 25	t 10 %	t 15 %	t 20 %

For each thickness range the manufacturer may adjust the beam power to achieve the required depth of penetration.

8.5.2.2 Diameter of the pipe

A procedure test carried out on a diameter "D" shall qualify the diameters for the range of qualification shown in Table 5.

Table 5 — Range of qualification for diameter

"D" diameter of the test piece	Range of qualification
D	0,75 D

8.6 Related to the filler materials

The qualified WPS is valid only for the approved filler material (grade or designation, shape and sizes).

8.7 Related to the joint geometry

The qualified WPS is valid only for the joint geometry and within the limits of clearance and misalignment defined in the welding procedure specification, according to joint design in 4.5 of prEN ISO 15609-3:2000 for electron beam welding and of prEN ISO 15609-4:2000 for laser beam welding.

8.8 Related to the presence of a weld backing

The qualified WPS is valid only insofar as no backing is added or removed.

The following shall be considered as a backing :

an external backing plate ;

a weld support machined on one of the workpieces ;

welding of the root of the test piece with a process other than electron or laser beam welding.

In the latter case, the conditions for the execution of the weld deposit remain associated with the qualification test and therefore they cannot be modified.

8.9 Related to the weld type

The qualification of a WPS obtained is valid only for the weld type used during the procedure test, i.e "full penetration" or "partial penetration".

8.10 Related to the welding position

The qualification of a WPS obtained is valid only for the welding position (defined according to EN ISO 6947) used during the procedure test.

8.11 Related to the welding parameters

8.11.1 Electron beam welding

The qualification of a WPS obtained is valid only insofar as the specified ranges of the welding parameters defined in the WPS (see 4.13 in prEN ISO 15609-3:2000) and the tolerances specified are met.

8.11.2 Laser beam welding

The qualification of a WPS obtained is valid only insofar as the specified range of the welding parameters defined in the WPS (see 4.13 in prEN ISO 15609-4:2000) and the tolerances specified are met.

8.12 Related to preheating

When a procedure includes preheating, it is not permissible :

to delete it ;

to decrease or increase the temperature out of the range defined by the WPS.

8.13 Related to post weld heat treatment

It is not permissible :

to delete a post weld heat treatment ;

to decrease or increase the temperature or duration out of the range defined by the WPS.

8.14 Related to the number of passes

The qualification of a WPS obtained is valid only insofar as the number of passes is the same as the one used for the procedure test.

8.15 Duration of validity

The duration of validity of the welding procedure qualification is unlimited provided that no major modification of the welding machine has been made.

9 Welding Procedure Qualification Record (WPQR)

The Welding Procedure Qualification Record (WPQR) is a statement of the results of assessment of each test piece including re-tests. The relevant items listed for the WPS in clause 4 of this standard shall be included, together with details of any features that would be rejectable by the requirements of clause 7.

If no rejectable features or unacceptable test results are found, a WPQR detailing the welding procedure test piece results is qualified and shall be signed and dated by the examiner or examining body.

A WPQR format shall be used to record details for the welding procedure and the test results, in order to facilitate uniform presentation and assessment of the parameters.

An example of the WPQR format is shown in annex A.

Annex A
(informative)

Welding Procedure Qualification Record form (WPQR)

Welding procedure qualification - Test certificate

Manufacturer's welding procedure Reference No:	Examiner or examining body Reference No:
Manufacturer:	
Address:	
Code/Testing standard:	
Date of welding:	

Extent of qualification

Welding process:

Equipment type:

Joint type:

Depth of penetration:

Parent metal (s):

Material thickness (mm):

Outside diameter (mm):

Filler metal type (if any):

Vacuum:

Shielding gas: Plasma gas : Backing gas :

Welding position:

Preheat:

Post-weld heat treatment and/or heat treatment:

Other information:

Certified that test welds prepared, welded and tested satisfactorily in accordance with the requirements of the code/testing standard indicated above.

.....	Examiner or examining body
Location	Date of issue
		Name, date and signature

Details of weld test

Welding procedure specification

See annex A of prEN ISO 15609-3:2000 for electron beam welding and of prEN ISO 15609-4:2000 for laser beam welding.

Test results

Identification of the test piece :

Non destructive examination :

carried out by :

. Visual examination : required Yes No
 . Radiographic examination : required Yes No
 Film type : Mark :
 . Ultrasonic examination : required Yes No
 . Penetrant testing : required Yes No

Without defect	With defect	
	Acceptable	Not acceptable

Destructive tests :

. Transverse tensile test : required Yes No

carried out by :

Type of test specimen : Normal Reduced Machined flush weld : Yes No

Test specimen		Size	Rm N/mm2	% Elongation	Fracture location			Remarks
Mark	Type				Parent material	HAZ	Weld metal	

. Bend test : carried out by :

Transverse required Yes No
 Longitudinal required Yes No

Test specimen		Specimen Size mm	Ø of mandrel mm	Loading span mm	Bending conditions			Bend angle	Remarks
Mark	Type				Face	Root	Side		

Identification of the test piece :

. Impact test : required Yes No

carried out by :

Identification mark	Section at root of notch cm ²	Temperature °C	Location				K		Remarks
			Test specimen		Notch		J/cm ²		
			Centre	Surface	WM	HAZ	Individual	Average	

WM : Weld Metal
HAZ : Heat Affected Zone

. Hardness test : required Yes No

carried out by :

Sketch of the test specimen	Traverse N°	Results

. Metallographic examination : required Yes No

carried out by :

Other tests carried out by

The tests were made in accordance with :

Test report N°

Test results are acceptable : Yes No

.....

Examiner or examining body

Tests carried out in presence of :

Name, date and signature

Annex ZA
(normative)

**List of ISO corresponding standards to European Standards given in clause
2**

European Standard given in clause 2	ISO standard corresponding	Title of ISO standard
EN 895	ISO 4136	Destructive tests on welds in metallic materials — Transverse tensile test
EN 910	ISO 5173	Destructive tests on welds in metallic materials — Bend tests
EN 970	ISO/DIS 17637	Non-destructive examination of fusion welds — Visual examination
EN 1043-2	ISO/DIS 9015-2	Destructive test on welds in metallic materials — Hardness test — Part 2 : Micro hardness testing on welded joints
EN 1290	ISO/DIS 17638	Non-destructive examination of welds — Magnetic particle examination of welds
EN 1321	ISO/DIS 17639	Non-destructive examination of fusion welds — Macroscopic and microscopic examination of welds
EN 1435	ISO/DIS 17636	Non-destructive examination of welds — Radiographic examination of welded joints
EN 1714	ISO/DIS 17640	Non destructive examination of welds — Ultrasonic examination of welded joints

Annex ZB (informative)

Clauses of this European Standard addressing essential requirements or other provisions of EU directives

This European Standard has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association and supports essential requirements of EU Directive 97/23/EEC.

WARNING Other requirements and other EU Directives may be applicable to the product(s) falling within the scope of this standard.

The following clauses of this standard are likely to support requirements of EU Directive 97/23/EEC.

Compliance with the clauses of this standard provides one with means of conforming with the specific essential requirements of the Directive concerned and associated EFTA regulations.

Table ZB.1 – Relation between this European Standard and the Directive 97/23/EEC

Clauses/Paragraphs of this European Standard	Essential requirement of the Directive 97/23/EEC	Comments/Notes
All clauses	Annexe I, 3.1.2	Permanent joining

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001.

Fax: +44 (0)20 8996 7001. Email: orders@bsi-global.com. Standards are also available from the BSI website at <http://www.bsi-global.com>.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre. Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: info@bsi-global.com.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001. Email: membership@bsi-global.com.

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsi-global.com/bsonline>.

Further information about BSI is available on the BSI website at <http://www.bsi-global.com>.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager. Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553. Email: copyright@bsi-global.com.