
Thermal spraying — Coatings for protection against corrosion and oxidation at elevated temperatures

The European Standard EN ISO 17834:2003 has the status of a
British Standard

ICS 25.220.20

National foreword

This British Standard is the official English language version of EN ISO 17834:2003. It is identical with ISO 17834:2003.

The UK participation in its preparation was entrusted to Technical Committee STI/40, Thermally sprayed inorganic finishes, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible international/European committee any enquiries on the interpretation, or proposals for change, and keep the UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this committee can be obtained on request to its secretary.

Cross-references

The British Standards which implement international or European publications referred to in this document may be found in the BSI Catalogue under the section entitled “International Standards Correspondence Index”, or by using the “Search” facility of the BSI Electronic Catalogue or of British Standards Online.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Summary of pages

This document comprises a front cover, an inside front cover, the EN ISO title page, pages 2 to 8, an inside back cover and a back cover.

The BSI copyright notice displayed in this document indicates when the document was last issued.

Amendments issued since publication

| Amd. No. | Date | Comments |
|----------|------|----------|
| | | |
| | | |
| | | |
| | | |

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 12 December 2003

© BSI 12 December 2003

ISBN 0 580 43087 1

ICS 25.220.20

English version

Thermal spraying - Coatings for protection against corrosion and oxidation at elevated temperatures (ISO 17834:2003)

Projection thermique - Revêtements de protection contre la corrosion et l'oxydation à haute température (ISO 17834:2003)

Thermisches Spritzen - Beschichtungen zum Schutz gegen Korrosion und Oxidation bei erhöhten Temperaturen (ISO 17834: 2003)

This European Standard was approved by CEN on 7 August 2003.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

Foreword.....3

1 Scope3

2 Normative references3

3 Coating material and processes.....4

4 Application of coating5

5 Required characteristics.....6

5.1 Coating thickness.....6

5.2 Service temperature, environment and subsequent treatment6

6 Re-treatment of defective areas6

Annex A (informative) Design recommendations for objects to be metal sprayed.....7

Annex B (normative) Coating materials.....8

Foreword

This document EN ISO 17834:2003 has been prepared by Technical Committee CEN/TC 240 "Thermal spraying and thermally sprayed coatings", the secretariat of which is held by DIN, in collaboration with Technical Committee ISO/TC 107 "Metallic and other inorganic coatings".

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2004, and conflicting national standards shall be withdrawn at the latest by June 2004.

Annex A is informative. Annex B is normative.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Spain, Sweden, Switzerland and the United Kingdom.

1 Scope

This standard is applicable to sprayed metal coatings for protection against corrosion at temperatures up to 1000°C (1273 K).

For the protection of iron and steel by sprayed aluminium and zinc coatings against atmospheric corrosion reference should be made to prEN ISO 2063.

Coating materials other than metals, although they may be applied by spraying, are outside the scope of this standard.

2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text, and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

EN 1274, Thermal spraying — Powders — Composition — Technical supply conditions.

EN 13507, Thermal spraying — Pre-treatment of surfaces of metallic parts and components for thermal spraying.

prEN ISO 2063, Thermal spraying — Metallic and other inorganic coatings — Zinc, aluminium and their alloys (ISO/DIS 2063:2002).

EN ISO 14919, Thermal spraying — Wires, rods and cords for flame and arc spraying — Classification — Technical supply conditions (ISO 14919:2001).

ISO 14232, Thermal spraying — Powders — Composition and technical supply conditions.

3 Coating material and processes

When selecting coating materials and processes, consideration shall be given to the different working temperatures and operating environments that may be found.

For example in any temperature range a coating may be required to resist:

- oxidation;
- other chemical attacks or;
- a combination of oxidation and other chemical attacks.

Typical coating materials will include the following:

- nickel/chromium alloys;
- iron/chromium/aluminium alloys;
- metal/chromium/aluminium/yttrium alloys.

NOTE The metal can be nickel, cobalt, iron or alloys of these.

Other inert wear resistant materials such as chromium carbide, may be blended with these alloys to provide a combination of properties.

When selecting coating materials, the following reactants and their effects either individually or when combined shall be considered:

- oxygen;
- sulphur;
- chlorine;
- vanadium;
- potassium;
- sodium.

Taking each of these in turn, the following points shall be considered:

- a) depending upon the presence or absence of oxygen, the corrosion characteristic can change significantly. Purely oxidising conditions indicate the use of aluminium alone;
- b) where high sulphur contents (mass fraction > 0,5 %) are present, the use of iron based alloys is recommended rather than nickel based unless their chromium content is a mass fraction > 30 %;
- c) where high chlorine contents (mass fraction > 0,5 %) are present, the use of nickel based alloys is recommended rather than iron based unless their chromium content is a mass fraction > 30 %;
- d) molten salts such as sodium or potassium vanadate require the addition of chromium to iron based materials. The chromium content shall be a mass fraction > 25 % and the aluminium content a mass fraction > 0,5 %;
- e) generally coating thicknesses of 0,2 mm shall be considered for aluminium and 0,4 mm for other materials.

With regard to the choice of process, the oxidation resistance of chromium bearing alloys is inversely related to the amount of chromium lost to oxide formed during the spraying process and the level of porosity. Therefore processes that create lower oxide and porosity levels will tend to perform better than others. Nevertheless this should be balanced against the fitness for purpose of the coating and economic factors.

4 Application of coating

The coating shall be applied to the clean and dry surface, prepared in accordance with EN 13507.

The sprayed coating shall be applied as soon as possible after surface preparation and before visible deterioration of the surface has occurred. If in comparison with a freshly prepared surface of material of similar quality visible deterioration has occurred, the surface preparation shall be repeated. In no case shall delay between surface preparation and coating application exceed 4 h unless special precautions, agreed between manufacturer and purchaser, are taken to ensure a suitably controlled storage atmosphere.

NOTE An initial thin coating of the sprayed metal can be applied to preserve the prepared surface; the requirements of clause 6 would then apply.

The surface of the sprayed coating shall be of uniform texture free from lumps, coarse areas and loosely adherent particles.

Contamination or corrosion of the sprayed coating shall be avoided at all stages during the application of the coating and the coating shall be maintained in a dry and clean condition until any subsequent treatment according to the requirements of clause 5 has been applied.

Table 1 — Coatings requirements and treatments for classes of service conditions

| Class | Service Temperature ^a and environment | Sprayed coating | | Subsequent treatment Intermediate/final treatment |
|----------------|---|--------------------------------------|---------------------------------|---|
| | | Coating material (see annex B) | Nominal coating thickness | |
| | | | | |
| A ^b | 350°C to 550°C | 1,2 | mm > 0,2 | may be sealed with silicone sealer |
| B ^b | Oxidising 350°C to 900°C Oxidising Up to 1000°C | 2 | > 0,2 | |
| C | (in absence of sulphurous gases or chlorine or molten salts) Up to 1000°C | 3,4,5 | > 0,4 | — |
| D | (in presence of sulphurous gases but not chlorine) Up to 1000°C | 4,5 | > 0,4 | — |
| E | (in presence of sulphurous gases and chlorine) | 5 | > 0,4 | — |
| F | For complex severe corrosion conditions | 6 | > 0,1 | may be diffusion heat treated in inert atmosphere |

a Provided it is realised that the service life will be affected, higher temperatures than those quoted may be tolerated. The reduction in service life will depend on the duration of the higher temperatures.

b At temperatures below 350°C in purely oxidising conditions the choice of coating material is not critical.

5 Required characteristics

5.1 Coating thickness

The nominal coating thickness shall be as given in Table 1 for the appropriate class of coating. When determined by the method described in prEN ISO 2063, the minimum local coating thickness shall be not less than 75 % of the specified nominal coating thickness, and the maximum local coating thickness shall not exceed the specified nominal coating thickness by more than 0,1 mm.

Coating thickness measurements shall be taken after the application of each coating metal and before any subsequent treatment is applied.

5.2 Service temperature, environment and subsequent treatment

Requirements on service temperature, environment and subsequent treatment are given in Table 1.

6 Re-treatment of defective areas

Any area found to be defective immediately prior to subsequent treatment shall be blasted clean of all sprayed metal prior to respraying, except that where the rejection has been solely due to too thin a coating, sprayed metal of the same quality may be added, provided that the surface has been kept dry and is free from visible contamination.

Annex A

(informative)

Design recommendations for objects to be metal sprayed

Components and structures to be metal sprayed should be designed from the outset with thermal spraying clearly in mind. Failure to do so is almost certain to increase the difficulties and cost of application and also to reduce the overall service life.

Three major guiding principles should be observed:

- a) design should ensure that all surfaces are fully accessible for surface preparation and permit complete and uniform application of the sprayed coatings;
- b) structure should be designed so that corrosion and oxidation have the greatest difficulty in establishing any focal point from which they can spread. This requirement demands cleanness of design and the elimination of all features that might facilitate lodgement or retention of foreign matter;
- c) the overall design should be planned to facilitate full inspection, ease of cleaning and maintenance.

Annex B
(normative)

Coating materials

Table B.1 — Coating materials

| Code of the coating material (see Table 1) | Material type | Standard |
|--|---|----------------------------------|
| 1 | Flame sprayed aluminium | EN ISO 14919 |
| 2 | Arc sprayed aluminium | EN ISO 14919 |
| 3 | nickel based alloys with chromium content 15 % | EN ISO 14919, EN 1274, ISO 14232 |
| 4 | iron based alloys with chromium content 25 % | EN ISO 14919, EN 1274, ISO 14232 |
| 5 | nickel based alloys with chromium content 30 % | EN ISO 14919, EN 1274, ISO 14232 |
| | | |
| 6 | metal ^a /chromium/aluminium/yttrium alloys | EN 1274, ISO 14232 |

a The metal may be nickel, cobalt, iron or alloys of these.

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001. Fax: +44 (0)20 8996 7001. Email: orders@bsi-global.com. Standards are also available from the BSI website at <http://www.bsi-global.com>.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre. Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: info@bsi-global.com.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001. Email: membership@bsi-global.com.

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsi-global.com/bsonline>.

Further information about BSI is available on the BSI website at <http://www.bsi-global.com>.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager. Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553. Email: copyright@bsi-global.com.

