

# Footwear — Test method for stiffeners and toepuffs — Bondability

The European Standard EN ISO 20863:2004 has the status of a  
British Standard

ICS 61.060

## National foreword

This British Standard is the official English language version of EN ISO 20863:2004. It is identical with ISO 20863:2004.

The UK participation in its preparation was entrusted to Technical Committee TCI/69, Footwear and leather, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible international/European committee any enquiries on the interpretation, or proposals for change, and keep the UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this committee can be obtained on request to its secretary.

### Cross-references

The British Standards which implement international or European publications referred to in this document may be found in the *BSI Catalogue* under the section entitled “International Standards Correspondence Index”, or by using the “Search” facility of the *BSI Electronic Catalogue* or of British Standards Online.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

**Compliance with a British Standard does not of itself confer immunity from legal obligations.**

### Summary of pages

This document comprises a front cover, an inside front cover, the EN ISO title page, pages 2 to 8, an inside back cover and a back cover.

The BSI copyright notice displayed in this document indicates when the document was last issued.

### Amendments issued since publication

Amd. No.	Date	Comments

ICS 61.060

English version

**Footwear - Test method for stiffeners and toepuffs - Bondability  
(ISO 20863:2004)**

Chaussures - Méthodes d'essai pour cotreforts et renforts -  
Aptitude au collage (ISO 20863:2004)

Schuhe - Prüfverfahren für Hinterkappen und Zehenkappen  
- Klebefestigkeit (ISO 20863:2004)

This European Standard was approved by CEN on 23 August 2004.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**Management Centre: rue de Stassart, 36 B-1050 Brussels**

## Contents

	<b>Page</b>
Foreword.....	3
1 Scope .....	4
2 Normative references .....	4
3 Terms and definitions .....	4
4 Apparatus and materials.....	4
5 Sampling and conditioning.....	5
5.1 Method 1: Heat activated materials.....	5
5.2 Method 2: Solvent activated materials .....	5
6 Procedure .....	5
7 Expression of results .....	6
7.1 Dry bondability.....	6
7.2 Wet bondability .....	6
8 Test report .....	7
<b>Annex ZA (normative) Normative references to International publications with their corresponding European publications.....</b>	<b>8</b>

## Foreword

This document (EN ISO 20863:2004) has been prepared by Technical Committee CEN/TC 309 "Footwear", the secretariat of which is held by AENOR, in collaboration with Technical Committee ISO/TC 216 "Footwear".

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2005, and conflicting national standards shall be withdrawn at the latest by June 2005.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

## 1 Scope

This document specifies a method for the determination of the bondability of heat activated and solvent activated stiffeners and toepuffs to upper and lining materials.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 12222, *Footwear — Standard atmospheres for conditioning and testing of footwear and components for footwear.*

EN ISO 3696, *Water for analytical laboratory use — Specification and test methods (ISO 3696:1987).*

EN ISO 4048, *Leather — Determination of matter soluble in dichloromethane (ISO 4048:1977).*

EN ISO 7500-1, *Metallic materials — Verification of static uniaxial testing machines — Part 1: Tension/compression testing machines — Verification and calibration of the force-measuring system (ISO 7500-1:2004).*

## 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

### **bondability**

aptitude of a material to be bonded to it self or to other material by applying pressure and/or heat and eventually adhesive.

## 4 Apparatus and materials

### 4.1 General

The following apparatus and materials shall be used.

**4.2 Tensile testing machine** with a jaw separation rate of 100 mm/min  $\pm$  10 mm/min, an appropriate force range (this will usually be less than 100 N), capable of measuring the force to an accuracy of better than 2 % as specified by class 2 in EN ISO 7500-1, which registers the force applied in terms of the displacement.

**4.3 Press knife** or other means of cutting rectangular test specimens of (150 mm  $\pm$  10mm) x (30 mm  $\pm$  2 mm).

**4.4 Press** with the following characteristics.

**4.4.1** Heated plates which can maintain a pre-established temperature with a precision of  $\pm$  5 °C.

**4.4.2** Operating pressure of 245 kPa  $\pm$  5 kPa (245 kPa are 2,5 kg/cm<sup>2</sup>).

**4.5 Reference leather**, full chrome splits (thickness of 1,5 mm to 1,7 mm) with a grease content of 4 % in total fat and 1 % in fatty acid (see EN ISO 4048).

**4.6 Non-woven fabric**, 150 g  $\pm$  20 g per square metre.

4.7 **Water distilled** or deionised complying with grade 3 of EN ISO 3696.

## 5 Sampling and conditioning

### 5.1 Method 1: Heat activated materials

5.1.1 Cut sufficient strips of (150 mm  $\pm$  10 mm) x (30 mm  $\pm$  2 mm) from the sample and the corresponding strips of the same size from the non-woven fabric and the reference leather (4.5) or the material to be used.

5.1.2 Make a "compound test piece" of leather-sample-non-woven fabric. A strip of paper is placed on one of the short sides between the leather and the sample, so that 20 mm remain unstuck and so that the ends can be held in the jaws of the tensile testing machine.

NOTE The side of the material to be tested should be that in contact with the standard leather, i.e. the side that in the shoe will be in contact with the upper leather.

5.1.3 Unless the manufacture establishes the application conditions, follow the Clauses 5.1.4 and 5.1.5.

5.1.4 Place the compound test piece between both press plates heated to 70 °C  $\pm$  5 °C, and apply a pressure of 245 kPa  $\pm$  5 kPa for 10 s.

5.1.5 Repeat the procedure described in sections 5.1.2 and 5.1.4 with the other test pieces and both press plates heated to 90 °C  $\pm$  5 °C, 110 °C  $\pm$  5 °C, 130 °C  $\pm$  5 °C and 150 °C  $\pm$  5 °C, respectively.

5.1.6 Condition the set test pieces in a conditioned environment as specified in EN 12222 for 24 h.

### 5.2 Method 2: Solvent activated materials

5.2.1 Cut at least two strips of (150 mm  $\pm$  10 mm) x (30 mm  $\pm$  2 mm) from the sample and two strips of the same size from the non-woven fabric and the reference leather (4.5) or the material to be used.

5.2.2 Activate the test specimen by applying acetone or other solvent (4.7) to it until it is uniformly wetted, then leave it for 2,5 min  $\pm$  0,5 min.

5.2.3 Make a "compound test piece" of leather-sample-non-woven fabric. A strip of paper is placed on one of the short sides between the leather and the sample, so that 20 mm remain unstuck and so that the ends can be held in the jaws of the tensile testing machine.

5.2.4 Unless the manufacturer establishes the application conditions, place the compound test piece between both press plates heated to 50 °C  $\pm$  5 °C, and apply a pressure of 245 kPa  $\pm$  5 kPa for 10 s (245 kPa are 2,5 kg/cm<sup>2</sup>).

5.2.5 Condition the set test pieces in a conditioned environment as specified in EN 12222 for 24 h.

## 6 Procedure

6.1 Fix the reference leather of the compound test piece in one of the jaws of the tensile testing machine and the end of the sample and the non-woven fabric in the other jaw.

6.2 Operate the tensile testing machine so that the jaw separates at a speed of 100 mm/min  $\pm$  10 mm/min.

6.3 Stop the tensile testing machine when half the length of the test piece has been unbonded.

6.4 Repeat the procedure described in 6.1, 6.2 and 6.3 with the other test pieces.

6.5 Submerge the part of the test pieces which are still bonded, in distilled water for 16 h.

6.6 Remove a test piece from the water, hold the free ends of the wet test piece in the jaws of the tensile testing machine and unbond the rest of the test piece.


6.7 Repeat the procedure described in 6.6 with the other test pieces.

## 7 Expression of results

### 7.1 Dry bondability

7.1.1 Calculate the average value of force (see Figure 1) obtained for 6.3 and 6.4 for each one of the test pieces, in newtons.

7.1.2 Divide the average value of force obtained for each one of the test pieces by the width of the test piece, measured in millimetres, and express the dry bondability, in newtons per millimetre.



#### Key

- 1 Force, in N
- 2 Average
- 3 Deformation

Figure 1 — Example of diagram force/deformation

### 7.2 Wet bondability

7.2.1 Calculate the average value of force obtained for 6.6 and 6.7 for each one of the wet test pieces, in newtons.

7.2.2 Divide the average value of force obtained in each one of the test pieces by the width of the test pieces, measured in millimetres, and express the wet bondability in newtons per millimetre.

## 8 Test report

The test report shall include the following information:

- a) reference to this document; EN ISO 20863;
- b) a description of the samples tested, including commercial styles, codes, colours, nature, etc.;
- c) the average dry bondability or the average for each temperature tested as shown in 7.1;
- d) the average wet bondability or the average for each temperature tested as shown in 7.2;
- e) date of testing;
- f) any deviation from this standard test method.

## Annex ZA (normative)

### Normative references to International publications with their corresponding European publications

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

<u>Publication</u>	<u>Year</u>	<u>Title</u>	<u>EN</u>	<u>Year</u>
ISO 3696	1987	Water for analytical laboratory use — Specification and test methods.	EN ISO 3696	1995
ISO 4048	1977	Leather — Determination of matter soluble in dichloromethane	EN ISO 4048	1998
ISO 7500-1	2004	Metallic materials — Verification of static uniaxial testing machines — Part 1: Tension/compression testing machines — Verification and calibration of the force-measuring system.	EN ISO 7500-1	2004
ISO 18454	2001	Footwear — Standard atmospheres for conditioning and testing of footwear and components for footwear	EN 12222	1997



---

## **BSI — British Standards Institution**

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

### **Revisions**

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

### **Buying standards**

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001. Fax: +44 (0)20 8996 7001. Email: [orders@bsi-global.com](mailto:orders@bsi-global.com). Standards are also available from the BSI website at <http://www.bsi-global.com>.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

### **Information on standards**

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre. Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: [info@bsi-global.com](mailto:info@bsi-global.com).

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001. Email: [membership@bsi-global.com](mailto:membership@bsi-global.com).

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsi-global.com/bsonline>.

Further information about BSI is available on the BSI website at <http://www.bsi-global.com>.

### **Copyright**

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager. Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553. Email: [copyright@bsi-global.com](mailto:copyright@bsi-global.com).