

Dentistry — Membrane materials for guided tissue regeneration in oral and maxillofacial surgery — Contents of a technical file

The European Standard EN ISO 22803:2005 has the status of a British Standard

ICS 11.060.15

National foreword

This British Standard is the official English language version of EN ISO 22803:2005. It is identical with ISO 22803:2004.

The UK participation in its preparation was entrusted by Technical Committee CH/106, Dentistry, to Subcommittee CH/106/8, Dental implants, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible international/European committee any enquiries on the interpretation, or proposals for change, and keep UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this subcommittee can be obtained on request to its secretary.

Cross-references

The British Standards which implement international or European publications referred to in this document may be found in the *BSI Catalogue* under the section entitled “International Standards Correspondence Index”, or by using the “Search” facility of the *BSI Electronic Catalogue* or of British Standards Online.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Summary of pages

This document comprises a front cover, an inside front cover, the EN ISO title page, the EN ISO foreword page, the ISO title page, pages ii to iv, pages 1 to 7 and a back cover.

The BSI copyright notice displayed in this document indicates when the document was last issued.

Amendments issued since publication

Amd. No.	Date	Comments

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 13 January 2006

© BSI 13 January 2006

English Version

**Dentistry - Membrane materials for guided tissue regeneration in
oral and maxillofacial surgery - Contents of a technical file (ISO
22803:2004)**

Art dentaire - Membranes pour régénération de tissus en
chirurgie buccale et maxillo-faciale - Contenu du dossier
technique (ISO 22803:2004)

Zahnheilkunde - Membranmaterialien für die gesteuerte
Gewebereneration bei oralen und maxillofazialen
Eingriffen - Inhalt der Technischen Dokumentation (ISO
22803:2004)

This European Standard was approved by CEN on 7 October 2005.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Foreword

The text of ISO 22803:2004 has been prepared by Technical Committee ISO/TC 106 "Dentistry" of the International Organization for Standardization (ISO) and has been taken over as EN ISO 22803:2005 by Technical Committee CEN/TC 55 "Dentistry", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2006, and conflicting national standards shall be withdrawn at the latest by May 2006.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

Endorsement notice

The text of ISO 22803:2004 has been approved by CEN as EN ISO 22803:2005 without any modifications.

INTERNATIONAL STANDARD

ISO
22803

First edition
2004-09-01

Dentistry — Membrane materials for guided tissue regeneration in oral and maxillofacial surgery — Contents of a technical file

*Art dentaire — Membranes pour régénération de tissus en chirurgie
buccale et maxillo-faciale — Contenu du dossier technique*



Reference number
ISO 22803:2004(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 22803 was prepared by Technical Committee ISO/TC 106, *Dentistry*, Subcommittee SC 8, *Dental implants*.

Introduction

Different materials used for the preservation of masticatory function, such as dental restorative materials and dental implants are subject to standards and regulations, either in existence or in preparation, designed to evaluate the performance of these products.

Membrane materials for periodontal tissue reconstruction in oral and maxillofacial surgery are not covered by the procedures for evaluating and testing dental restorative materials and dental implants, thus it is necessary to develop a new International Standard for these materials.

The aim of this International Standard is to define the content of a technical file that demonstrates safety and effectiveness of membrane materials used in oral and maxillofacial surgery.

Dentistry — Membrane materials for guided tissue regeneration in oral and maxillofacial surgery — Contents of a technical file

1 Scope

This International Standard gives the requirements for a technical file on the evaluation of the chemical, physical, mechanical, biological and clinical aspects and behaviour of membrane materials, whether resorbable, partially resorbable or non-resorbable, which are used

- for guided tissue regeneration in oral and maxillofacial surgery to correct a morphological defect or abnormality,
- in contact with teeth and/or dental implants,
- for prevention of epithelial migration in periodontal surgery,
- for the augmentation of bone prior to the planned insertion of dental implants,
- and/or for augmentation of bone for stabilization of dental prostheses.

This International Standard is not applicable to materials whose primary intended use is to deliver a medicinal product, autografts and allografts, or materials intended to act through pharmacological, immunological or metabolic means.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1942, *Dentistry — Vocabulary*¹⁾

ISO 10993-1, *Biological evaluation of medical devices — Part 1: Evaluation and testing*

ISO 10993-7, *Biological evaluation of medical devices — Part 7: Ethylene oxide sterilization residuals*

ISO 11134, *Sterilization of health care products — Requirements for validation and routine control — Industrial moist heat sterilization*

ISO 11135, *Sterilization of health care products — Ethylene oxide — Requirements for development, validation and routine control of a sterilization process for medical devices*

ISO 11137, *Sterilization of health care products — Requirements for validation and routine control — Radiation sterilization*

ISO 11607, *Packaging for terminally sterilized medical devices*

ISO 14155-1, *Clinical investigation of medical devices for human subjects — Part 1: General requirements*

ISO 14937, *Sterilization of health care products — General requirements for characterization of a sterilizing agent and the development, validation and routine control of a sterilization process for medical devices*

1) Revision of ISO 1942-1:1989, ISO 1942-2:1989, ISO 1942-3:1989, ISO 1942-4:1989 and ISO 1942-5:1989.

ISO 14971, *Medical devices — Application of risk management to medical devices*

ISO 15223, *Medical devices — Symbols to be used with medical device labels, labelling and information to be supplied*

EN 1041, *Information supplied by the manufacturer with medical devices*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 1942 and the following apply.

3.1
periodontal tissue
all tissues constituting the dental periodontium, i.e. alveolar bone, gingival tissue, periodontal ligament and cementum

3.2
biocompatibility
〈material action〉 capacity of a material to fulfill its function with an appropriate response for a specific application in the recipient

3.3
biocompatibility
〈material reaction〉 quality of being accepted in a specific living environment without adverse or unwanted side effects

[ISO 1942-1:1989/Amd.5:1993, definition 1.200]

3.4
biomaterial
〈general purpose〉 material intended to interface with the biological system to evaluate, treat, augment or replace tissue, organ or function of the organism

3.5
biomaterial
〈tailored preparation〉 material specially prepared and/or presented to exhibit bioacceptability, biocompatibility or positive biocompatibility

[ISO 1942-1:1989/Amd.5:1993, definition 1.204]

NOTE The implantable materials referred to in this International Standard are all biomaterials.

3.6
membrane material
medical device specifically prepared as a material which, when placed into tissue, carries out a barrier function

NOTE The sheet may be occlusive or selectively permeable to cells, macromolecules and/or fluid.

3.7
barrier
structure which, when placed into tissue, prevents the intermixing of the cell population on each side of the structure and/or prevents the prolapse of tissue

3.8
packing
surgical placement of a biomaterial to fill an intrabony cavity or defect

3.9

augmentation

surgical placement of autogenous bone and/or of a biomaterial, resorbable or non-resorbable, to increase the volume of a bone or bridging of a defect

3.10

resorbable

ability of a membrane material to undergo progressive elimination by cellular activity and/or dissolution in a biological environment

3.11

tissue regeneration

reproduction or reconstruction of a lost or injured tissue by induction, conduction or healing process

3.12

guided tissue regeneration

GTR

formation of tissue among which the orientation, the function, the volume and the place are pre-modelled by an exogenous mean

3.13

guided bone regeneration

GBR

bone formation specifically obtained by GTR principles

4 General description

Membrane materials are widely used in periodontology and oral and maxillofacial surgery, and have characteristics which are unique to these applications, for example:

- a) placement in contact with teeth and their supporting tissues;
- b) prevention of oral mucosal epithelial migration into surgically treated defects;
- c) predictable loss of structural integrity and mechanical properties over time in oral sites into which dental implants are to be subsequently placed;
- d) known behaviour of the material should it become inadvertently exposed to the oral or paranasal cavities subsequent to placement;
- e) augmentation of the volume or dimension of bone for enhanced stabilization of dentures or for placement of dental implants.

The development of membrane materials shall be considered with regard to the properties required for the intended purpose, taking into account the effects of manufacture, handling, sterilization and storage. Possible reactions (intended or not) of membrane materials with human tissues and body fluids, other materials, other implants, substances, gases, radiation and electromagnetic fields shall be considered.

Membrane materials for periodontal tissue reconstruction in oral and maxillofacial surgery are used as either a barrier or a covering of packing materials.

During their use, these materials can induce an acute inflammatory reaction, which must be evaluated by specific tests.

5 Contents of a technical file

5.1 General

The contents of a technical file shall include the following information about the membrane material:

- a) details of its chemical composition;
- b) its intended performance;
- c) its preclinical and clinical evaluations;
- d) details of its manufacture, sterilization and packaging;
- e) certain other items of information necessary for the user.

5.2 Chemical composition

Refer to ISO 10993-13, ISO 10993-14, ISO 10993-15 and ISO 10993-18 for guidance. All polymer characterization shall be completed after recommended sterilization procedures have been applied.

5.3 Intended performance

The intended performance of a membrane material shall be described and documented by addressing the following:

- general description of the product;
- functional characteristics: resorbable, partially resorbable or non-resorbable;
- typical intended applications: simple barrier (in this case give physical and mechanical characteristics, including deformability);
- completely submersed or not during use;
- intended conditions of use;
- whether the device is intended to be used with fixation;
- included physical additives (e.g. titanium);
- included chemical additives (e.g. mineral salts);
- included material degradation when undergoing multiple cycles of reprocessing;
- reference to published standards to which the device conforms, with particular regard to safety.

Account should be taken of

- published standards,
- published clinical and scientific literature,
- validated test results.

5.4 Preclinical and clinical evaluation

5.4.1 General

Following an appropriate risk analysis as part of a risk management programme in accordance with ISO 14971, membrane materials shall be evaluated to demonstrate that their intended performance is achieved in GTR and/or GBR. The extent to which the intended performance has been achieved shall be determined and documented. Safety shall be demonstrated by preclinical and clinical evaluations and testing, as appropriate.

5.4.2 Preclinical evaluation

All details of the preclinical evaluation shall be provided. Preclinical evaluation shall include both the physical and biological properties of the membrane materials.

Among its physical properties, the physical strength of the membrane in an artificial medium over a period of time, including its tear resistance, shall be determined, using appropriate methods.

The preclinical biological evaluation shall be carried out in accordance with ISO 10993-1 by

- a compilation and critical analysis of the relevant scientific literature; and
- if necessary, analysis of data obtained from tests performed.

Laboratory and, if necessary, animal tests should be designed to establish that the materials meet the requirements for their use in periodontal, oral and maxillofacial surgery. Such tests should include *in vitro* and *in vivo* studies aimed at establishing the biocompatibility of the membranes with the periodontal tissues and bone, their ability to inhibit or guide the migration of oral epithelial cells, their biodegradability by the host tissues and their behaviour when exposed to the oral environment, including the ability of oral and/or nasal micro-organisms to colonise them. Evidence to show that the membrane is compatible with devices and substances that would be encountered during intended uses shall be included.

5.4.3 Clinical evaluation

Details of the clinical evaluation shall be provided.

Membrane materials shall undergo clinical evaluation by

- a) a compilation and critical analysis of the relevant literature covering the intended clinical use of the materials, and/or
- b) an analysis of data obtained from clinical investigations of the specific membrane material, especially with regard to evidence of new bone formation, bone resorption and/or periodontal tissue regeneration.

If a clinical investigation is carried out, it shall be managed in accordance with the requirements of ISO 14155-1.

5.5 Manufacture

Manufacturing processes shall be described and evidence of their validation shall be provided.

Membrane materials shall be manufactured in such a way that the intended performance is achieved.

5.6 Sterilization

5.6.1 Products supplied sterile

The sterility assurance level of terminally sterilized membrane materials shall be 10^{-6} or better. Sterilization processes shall be validated and routinely controlled.

If membrane materials are to be sterilized by ethylene oxide, ISO 11135 shall apply; by irradiation, ISO 11137; by steam, ISO 11134; by any other method, validation shall be carried out according to ISO 14937.

If the manufacturer states that resterilization is acceptable, the maximum permissible number of cycles shall be stated and at least one validated method shall be specified.

For membrane materials that are supplied non-sterile, the manufacturer shall specify at least one validated method of sterilization such that their functional safety is not adversely affected. If multiple sterilizations are not allowed, this shall be stated in the information provided by the manufacturer (see 5.8).

5.6.2 Sterilization residuals

Testing for residuals of sterilization shall be in accordance with the principles set out in ISO 10993-1. The levels of residuals shall not exceed the limits specified in ISO 10993-7.

5.7 Packaging

5.7.1 Protection from damage in storage and transport

Details of packaging methods and materials shall be given and a sample package shall be provided.

The packaging shall be designed so that, under conditions specified by the manufacturer for storage, transport and handling (including control of temperature, humidity and ambient pressure, if applicable), it protects against damage and deterioration and the material is not adversely affected. Validation of this capability shall be referenced in the technical file.

5.7.2 Maintenance of sterility in transit

Membrane materials supplied in sterile conditions shall be packaged so that they remain sterile under normal storage, transport and handling conditions unless the package is damaged or opened.

For terminally sterilized products, packaging shall conform to ISO 11607.

5.8 Additional information supplied by the manufacturer

5.8.1 General

Information supplied by the manufacturer shall be in accordance with EN 1041. If symbols are used, they shall be in accordance with ISO 15223.

A copy of the instructions for use and product label shall be included. If the instructions for use are revised, the technical file should also include date of revision and/or revision number.

Validation of the product capability shall be referenced in the technical file.

5.8.2 Restrictions on combinations

If the membrane material is intended to be used in combination with other devices, any restrictions in the use of the combination shall be stated on the label or in the instructions for use.

5.8.3 Identification of membrane materials

In order to provide traceability, the following information shall be included on the primary package label:

- name of product;
- manufacturer's name or trademark;
- address of the manufacturer;
- batch code (lot number) or serial number;
- date of manufacture;
- sterile (plus method of sterilization) or not sterile;
- storage recommendation; and
- expiry date of sterility (if sterilized by manufacturer).

Bibliography

- [1] ISO 1942-1:1989/Amd.5:1993, *Dental vocabulary — Part 1: General and clinical terms — Amendment 5*
- [2] ISO 10993-2, *Biological evaluation of medical devices — Part 2: Animal welfare requirements*
- [3] ISO 10993-3, *Biological evaluation of medical devices — Part 3: Tests for genotoxicity, carcinogenicity and reproductive toxicity*
- [4] ISO 10993-4, *Biological evaluation of medical devices — Part 4: Selection of tests for interactions with blood*
- [5] ISO 10993-5, *Biological evaluation of medical devices — Part 5: Tests for in vitro cytotoxicity*
- [6] ISO 10993-6, *Biological evaluation of medical devices — Part 6: Tests for local effects after implantation*
- [7] ISO 10993-9, *Biological evaluation of medical devices — Part 9: Framework for identification and quantification of potential degradation products*
- [8] ISO 10993-10, *Biological evaluation of medical devices — Part 10: Tests for irritation and delayed-type hypersensitivity*
- [9] ISO 10993-11, *Biological evaluation of medical devices — Part 11: Tests for systemic toxicity*
- [10] ISO 10993-12, *Biological evaluation of medical devices — Part 12: Sample preparation and reference materials*
- [11] ISO 10993-13, *Biological evaluation of medical devices — Part 13: Identification and quantification of degradation products from polymeric medical devices*
- [12] ISO 10993-14, *Biological evaluation of medical devices — Part 14: Identification and quantification of degradation products from ceramics*
- [13] ISO 10993-15, *Biological evaluation of medical devices — Part 15: Identification and quantification of degradation products from metals and alloys*
- [14] ISO 10993-18, *Biological evaluation of medical devices — Part 18: Chemical characterization of materials*
- [15] ISO 13408-1, *Aseptic processing of health care products — Part 1: General requirements*
- [16] ISO 14160, *Sterilization of single-use medical devices incorporating materials of animal origin — Validation and routine control of sterilization by liquid chemical sterilants*
- [17] ISO/TR 14283, *Implants for surgery — Fundamental principles*
- [18] ISO 14630, *Non-active surgical implants — General requirements*
- [19] EN 980, *Graphical symbols for use in the labelling of medical devices*

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover.
Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001.
Fax: +44 (0)20 8996 7001. Email: orders@bsi-global.com. Standards are also available from the BSI website at <http://www.bsi-global.com>.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre.
Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: info@bsi-global.com.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration.
Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001.
Email: membership@bsi-global.com.

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsi-global.com/bsonline>.

Further information about BSI is available on the BSI website at <http://www.bsi-global.com>.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager.
Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553.
Email: copyright@bsi-global.com.
