

BS EN 61212-3-2:2013



BSI Standards Publication

Insulating materials — Industrial rigid round laminated tubes and rods based on thermosetting resins for electrical purposes

Part 3: Specifications for individual materials — Sheet 2: Round laminated moulded tubes

bsi.

...making excellence a habit.™

Licensed copy: Heriot-Watt. Heriot-Watt University Library. Version correct as of 29/01/2014

National foreword

This British Standard is the UK implementation of EN 61212-3-2:2013. It is identical to IEC 61212-3-2:2013. It supersedes BS EN 61212-3-2:2006, which will be withdrawn on 3 June 2016.

The UK participation in its preparation was entrusted by Technical Committee GEL/15, Solid electrical insulating materials, to Subcommittee GEL/15/6, Rigid fibrous reinforced laminates for electrical purposes.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2013.
Published by BSI Standards Limited 2013

ISBN 978 0 580 70403 1
ICS 29.035.01

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 August 2013.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

EUROPEAN STANDARD
 NORME EUROPÉENNE
 EUROPÄISCHE NORM

EN 61212-3-2

July 2013

ICS 29.035.01

Supersedes EN 61212-3-2:2006

English version

**Insulating materials -
 Industrial rigid round laminated tubes and rods based on thermosetting
 resins for electrical purposes -
 Part 3: Specifications for individual materials -
 Sheet 2: Round laminated moulded tubes
 (IEC 61212-3-2:2013)**

Matériaux isolants -
 Tubes et barres industriels rigides, ronds,
 stratifiés, à base de résines
 thermodurcissables, à usages électriques
 -
 Partie 3: Spécifications pour matériaux
 particuliers -
 Feuille 2: Tubes ronds stratifiés moulés
 (CEI 61212-3-2:2013)

Isolierstoffe – Runde Rohre und Stäbe
 aus technischen Schichtpressstoffen auf
 der Basis warmhärtender Harze für
 elektrotechnische Zwecke – Teil 3:
 Bestimmungen für einzelne Werkstoffe –
 Blatt 2: Runde, formgepresste Rohre
 (IEC 61212-3-2:2013)

This European Standard was approved by CENELEC on 2013-06-03. CENELEC members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CENELEC member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CENELEC member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CENELEC members are the national electrotechnical committees of Austria, Belgium, Bulgaria, Croatia, Cyprus, the Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, the Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

CENELEC

European Committee for Electrotechnical Standardization
 Comité Européen de Normalisation Electrotechnique
 Europäisches Komitee für Elektrotechnische Normung

Management Centre: Avenue Marnix 17, B - 1000 Brussels

Foreword

The text of document 15/700/FDIS, future edition 3 of IEC 61212-3-2, prepared by IEC/TC 15 "Solid electrical insulating materials", was submitted to the IEC-CENELEC parallel vote and approved by CENELEC as EN 61212-3-2:2013.

The following dates are fixed:

- latest date by which the document has (dop) 2014-03-03
to be implemented at national level by
publication of an identical national
standard or by endorsement
- latest date by which the national (dow) 2016-06-03
standards conflicting with the
document have to be withdrawn

This document supersedes EN 61212-3-2:2006.

EN 61212-3-2:2013 includes the following significant technical changes with respect to EN 61212-3-2:2006:

Details of test for insulation resistance after immersion in water are changed.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CENELEC [and/or CEN] shall not be held responsible for identifying any or all such patent rights.

Endorsement notice

The text of the International Standard IEC 61212-3-2:2013 was approved by CENELEC as a European Standard without any modification.

In the official version, for Bibliography, the following notes have to be added for the standards indicated:

- | | | |
|--------------------|------|---|
| IEC 61212-3 series | NOTE | Harmonized in EN 61212-3 series (not modified). |
| ISO 472:1999 | NOTE | Harmonized as EN ISO 472:2001 (not modified). |

Annex ZA
(normative)
Normative references to international publications
with their corresponding European publications

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

NOTE When an international publication has been modified by common modifications, indicated by (mod), the relevant EN/HD applies.

<u>Publication</u>	<u>Year</u>	<u>Title</u>	<u>EN/HD</u>	<u>Year</u>
IEC 61212-1	-	Insulating materials - Industrial rigid round laminated tubes and rods based on thermosetting resins for electrical purposes - Part 1: Definitions, designations and general requirements	EN 61212-1	-
IEC 61212-2	2006	Insulating materials - Industrial rigid round laminated tubes and rods based on thermosetting resins for electrical purposes - Part 2: Methods of test	EN 61212-2	2006

CONTENTS

INTRODUCTION.....	5
1 Scope.....	6
2 Normative references	6
3 Terms and definitions	6
4 Designations and abbreviations	7
4.1 General	7
4.2 Designation	7
4.3 Abbreviations	7
5 Requirements	7
Bibliography.....	13
Table 1 – Types of industrial round moulded tubes	8
Table 2 – Permissible deviation from nominal external diameter of round moulded tubes in the “as moulded” condition	8
Table 3 – Permissible deviation from nominal external diameter of moulded tubes in ground or turned condition, all types	9
Table 4 – Permissible deviation from nominal internal diameter of moulded tubes	9
Table 5 – Tolerance on wall thickness for round moulded tubes.....	9
Table 6 – Departure from straightness for round moulded tubes	10
Table 7 – Property requirements for round moulded tubes	11
Table 8 – Electric strength at 90 °C in oil, perpendicular to laminations for round moulded tubes (1 min proof test or 20 s step-by-step test) ^a (kV/mm).....	12

INTRODUCTION

This part of IEC 61212 is one of a series which deals with industrial rigid round laminated tubes and rods based on thermosetting resins for electrical purposes.

This series consists of three parts:

- Part 1: Definitions, designations and general requirements (IEC 61212-1)
- Part 2: Methods of test (IEC 61212-2)
- Part 3: Specifications for individual materials (IEC 61212-3)

IEC 61212-3-2 contains one of the specification sheets comprising Part 3, as follows:

Sheet 2: Round laminated moulded tubes.

INSULATING MATERIALS – INDUSTRIAL RIGID ROUND LAMINATED TUBES AND RODS BASED ON THERMOSETTING RESINS FOR ELECTRICAL PURPOSES –

Part 3: Specifications for individual materials – Sheet 2: Round laminated moulded tubes

1 Scope

This part of IEC 61212 gives requirements for industrial rigid round laminated moulded tubes for electrical purposes, based on different resins and different reinforcements.

Applications and distinguishing properties are given in Table 1.

Materials which conform to this specification meet established levels of performance. However, the selection of a material by a user for a specific application should be based on the actual requirements necessary for adequate performance in that application and not based on this specification alone.

Safety Warning:

It is the responsibility of the user of the methods contained or referred to in this document to ensure that they are used in a safe manner.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 61212-1, *Insulating materials – Industrial rigid round laminated tubes and rods based on thermosetting resins for electrical purposes – Part 1: Definitions, designations and general requirements*

IEC 61212-2:2006, *Insulating materials – Industrial rigid round laminated tubes and rods based on thermosetting resins for electrical purposes – Part 2: Methods of test*

3 Terms and definitions

For the purposes of this document, the following term and definition apply.

3.1

moulded tube

<thermosets> tube formed by rolling impregnated layers of material on a mandrel, curing the assembly in a cylindrical mould under heat and pressure, and then removing the mandrel

[SOURCE: ISO 472:1999, modified – In the ISO definition, the term “laminated moulded tube” is used instead of “moulded tube” and an indication “or other suitable” is provided between the words “cylindrical” and “mould”.]

4 Designations and abbreviations

4.1 General

The moulded tubes covered by this Part 3 sheet are classified into types which differ in the resin and reinforcement used, the method of manufacture and their distinguishing properties.

4.2 Designation

Individual types are designated by:

- a two-letter abbreviation denoting the resin;
- a second two-letter abbreviation, denoting the reinforcement;
- a serial number of two digits, the first digit denoting the form of the material, a "3" indicates moulded tubes, and, a second digit denoting sub-grades of the same type.

The abbreviations are given in 4.3.

The complete designation of the moulded tube is denoted by:

- description: moulded tube;
- number of the IEC standard: IEC 61212-3-2;
- designation of the individual type;
- dimensions (in millimetres) of the moulded tube:
internal diameter × external diameter × length;
- a letter designating the finish on the external diameter of the moulded tube:
"A" designating moulded tubes in the "as produced" condition;
"B" designating moulded tubes in ground or turned condition.

EXAMPLE Moulded tube, IEC 61212-3-2 – EP CC 31 – 25 × 35 × 1 000-A.

4.3 Abbreviations

Types of resin		Types of reinforcement	
EP	Epoxy (epoxide)	CC	Woven cotton cloth
PF	Phenolic	CP	Cellulosic paper

5 Requirements

In addition to the general requirements given in IEC 61212-1, the moulded tubes shall comply with the additional requirements given in Tables 2, 3, 4, 5, 6, 7, and 8, with the exception of the length of tube supplied, which shall be subject to agreement between buyer and seller.

Table 1 – Types of industrial round moulded tubes

Resin	Reinforcement	Serial number	Applications and distinguishing characteristics ^a
EP	CC	31	Mechanical, electrical and electronic applications. Good resistance to tracking. fine weave ^b .
PF	CC	31	Mechanical and electrical applications. fine weave ^b .
		32	Similar to type PF CC 31, but of coarse weave ^b .
		33	Similar to type PF CC 31, but of very coarse weave ^b .
	CP	31	Electrical and mechanical applications. Good electrical properties when exposed to normal relative humidity.
		32	Similar to type PF CP 31, but with improved mechanical and electrical properties.

^a It should not be inferred from the contents of Table 1 that round laminated moulded tubes of any particular type are necessarily unsuitable for applications other than those listed for them, or that specific round laminated moulded tubes will be suitable for all applications within the wide description given.

^b Fabric weaves of type CC reinforcements:

	Mass per unit area g/m ²	Thread count cm ⁻¹
Very coarse weave	> 200	< 18
Coarse weave	> 130	18 to 29
Fine weave	≤ 130	30 to 37
Very fine weave	≤ 125	> 37

These values are only for information. They are not to be considered as specification values. In general, the finer weave materials have better machining characteristics.

Table 2 – Permissible deviation from nominal external diameter of round moulded tubes in the “as moulded” condition

Nominal external diameter <i>D</i> mm	Maximum deviation, ± mm	
	Type	
	PF CP	EP CC PF CC
≤ 3	0,08	--
3 < <i>D</i> ≤ 6	0,1	--
6 < <i>D</i> ≤ 10	0,15	--
10 < <i>D</i> ≤ 20	0,2	0,3
20 < <i>D</i> ≤ 30	0,3	0,4
30 < <i>D</i> ≤ 50	0,3	0,4
50 < <i>D</i> ≤ 75	0,4	0,4
75 < <i>D</i> ≤ 100	0,5	0,5
100 < <i>D</i> ≤ 150	0,6	0,6
150 < <i>D</i> ≤ 200	0,7	0,7
200 < <i>D</i> ≤ 300	0,75	0,75
300 < <i>D</i> ≤ 500	0,8	0,8
> 500	1,0	1,0

Test method: see 4.1 of IEC 61212-2:2006.

NOTE A double dash "--" signifies that there is no requirement.

Table 3 – Permissible deviation from nominal external diameter of moulded tubes in ground or turned condition, all types

Nominal external diameter D mm	Maximum deviation ^a ± mm
≤ 25	0,15
25 < D ≤ 50	0,25
50 < D ≤ 75	0,30
75 < D ≤ 100	0,35
100 < D ≤ 125	0,45
> 125	0,50

Test method: see 4.2 of IEC 61212-2:2006.

^a If a unilateral tolerance is agreed between purchaser and supplier, the tolerance may not be greater than twice the value given in the table.

Table 4 – Permissible deviation from nominal internal diameter of moulded tubes

Nominal internal diameter d mm	Maximum deviation ^a ± mm
≤ 3	0,10 ^b
3 < d ≤ 30	0,15
30 < d ≤ 50	0,20
50 < d ≤ 75	0,25
75 < d ≤ 100	0,30
100 < d ≤ 150	0,50
150 < d ≤ 200	0,70
200 < d ≤ 300	1,00
300 < d ≤ 500	1,50
> 500	2,00

Test method: see 4.3 of IEC 61212-2:2006.

^a If a unilateral tolerance is agreed between purchaser and supplier, the tolerance may not be greater than twice the value given in the table.

^b Applicable to PF CP types only.

Table 5 – Tolerance on wall thickness for round moulded tubes

Nominal wall thickness t mm	Maximum deviation ± mm		
	Types		
	PF CP PF CP 32	EP CC PF CC 31	PF CC PF CC 33 PF CC 34
≤ 1,5	0,25	0,28	0,40
1,5 < t ≤ 3,0	0,40	0,45	0,60
3,0 < t ≤ 6,0	0,55	0,60	0,85
6,0 < t ≤ 12,0	0,90	1,00	1,35
12,0 < t ≤ 25,0	1,30	1,40	1,90
> 25,0	2,00	2,00	2,70

Test method: see 4.4 of IEC 61212-2:2006.

Table 6 – Departure from straightness for round moulded tubes

Nominal external diameter D mm	Maximum deviation mm
$D < 8$	$8 L^2$
$D \geq 8$	$6 L^2$

Test method: see 4.5 of IEC 61212-2:2006.

The departure from straightness of any tube shall not exceed the appropriate limiting value given above, where L is the length of the tube in metres.

Table 7 – Property requirements for round moulded tubes

Property	Method of Test IEC 61212-2:2006 (Subclause No.)	Unit	Maximum or minimum	Type						Remarks	
				EP CC 31	PF CC 31	PF CC 32	PF CC 33	PF CP 31	PF CP 32		
Flexural strength perpendicular to laminations	5.1	MPa	minimum	80	80	80	80	80	80	80	Generally applicable to tubes of internal diameter greater than 100 mm but to all tubes where satisfactory test pieces can be produced. For tubes of internal diameter less than 100 mm however the test for cohesion between layers is an alternative method.
Axial compressive strength	5.2	MPa	minimum	125	100	100	100	70	100		
Cohesion between layers	5.3	MPa	minimum	100	90	90	90	60	70		Applicable only to tubes of nominal internal diameter not greater than 100 mm.
Breakdown voltage at 90 °C in oil parallel to laminations	6.1	kV	minimum	40	5	5	5	10	30		The 20 s step-by-step test and the 1 min proof test for breakdown voltage at 90 °C in oil, parallel to laminations, are alternatives.
Electric strength at 90 °C in oil perpendicular to laminations	6.1	kV/mm	minimum	See Table 8							Applicable only to tubes of nominal wall thickness not greater than 3 mm.
Insulation resistance after immersion in water	6.2	MΩ	minimum	75	10	5	1	0,1	75		
Dissipation factor 1 MHz 48 Hz to 62 Hz	6.3	–	maximum	(0,05)	--	--	--	--	--		Conformance with the requirement for either test constitutes conformance with the specification in this respect.
Permittivity 1 MHz 48 Hz to 62 Hz	6.3	–	maximum	(6,0)	--	--	--	--	--		Conformance with the requirement for either test constitutes conformance with the specification in this respect.
Thermal endurance	7.1	TI		(130)	(120)	(120)	(120)	(120)	(120)		
Water absorption	7.2	mg/cm ²	maximum	3,0	5,0	6,0	8,0	8,0	3,0		
Density	7.3	g/cm ³	Range	(1,20 – 1,40)	(1,20 – 1,40)	(1,20 – 1,40)	(1,20 – 1,40)	(1,20 – 1,40)	(1,20 – 1,40)		

Values in brackets "()" are intended to give only general guidance and are not to be considered as requirement of this standard.

NOTE A double dash "--" signifies that there is no requirement.

Table 8 – Electric strength at 90 °C in oil, perpendicular to laminations for round moulded tubes (1 min proof test or 20 s step-by-step test)^a (kV/mm)

Type	Nominal wall thickness of test specimen ^b mm											
	1,0	1,2	1,4	1,6	1,8	2,0	2,2	2,4	2,5	2,6	2,8	3,0
EP CC 31	7,5	6,8	6,3	5,9	5,5	5,3	5,1	5,0	4,9	4,8	4,7	4,7
PF CC 31	2,4	2,3	2,2	2,1	2,1	2,0	1,9	1,9	1,8	1,8	1,7	1,6
PF CC 32	2,4	2,3	2,2	2,1	2,1	2,0	1,9	1,9	1,8	1,8	1,7	1,6
PF CC 33	--	--	--	--	--	2,0	1,9	1,9	1,8	1,8	1,7	1,6
PF CP 31	7,5	6,8	6,3	5,9	5,5	5,3	5,1	5,0	4,9	4,8	4,7	4,7
PF CP 32	9,7	9,0	8,2	7,8	7,4	7,0	6,7	6,5	6,4	6,3	6,2	6,1

Test method: see 6.1 of IEC 61212-2:2006.

NOTE A double dash "--" signifies that there is no requirement.

^a The requirements for the 20 s step-by-step test and the 1 min proof test for electric strength at 90 °C in oil, perpendicular to laminations, are alternatives. A material meeting either requirement is deemed to comply with the specification with respect to electric strength at 90 °C in oil, perpendicular to laminations.

^b If the nominal wall thickness of the test specimen lies between two values of wall thickness shown in the above table, the limit is obtained by interpolation. If the nominal wall thickness is below the minimum thickness for which a limit is given, the electric strength limit appropriate to the minimum thickness shall apply. For nominal wall thicknesses greater than 3,0 mm, the values for 3,0 mm shall apply.

Bibliography

IEC 61212-3 (all sheets), *Insulating materials – Industrial rigid round laminated tubes and rods based on thermosetting resins for electrical purposes – Part 3: Specifications for individual materials*

ISO 472:1999, *Plastics – Vocabulary*

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com